

TOTAL NET WT. _____		PKG. N-CODE _____

PROD. SPVR. _____	DATE _____	WHSE. OPER. _____

N37556

33/106

CG 50 CODE YT-562-D PKG.

→ JUL-14 80 36485
EST. WGT. 2375 255 LBS.

16

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES YT-562-D (P)	APPROVED BY BBK 01-16-78 AMJ 12-14-78
	TYPED BY emw121578	
	MAKING NOTES	
REMARKS		

NAME: GREEN GOLD

NON-BLEEDING

INSTRUCTIONS					-PRESSING-	RECORD				
VAT		106			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		7-14			STARTED	11:30 AM				
TIME		300 P			CAKES USED	62				
RELEASED BY		ADG			WATER ON	5:44 PM				
PRESS	32	33	35	36	HRS. WASHED	14 1/2				
NO. OF CAKES	60	60	60	64	OHMS	5006				
PRESS without					HRS. WASHED					
WASH TO	4000				OHMS					
TEST AFTER	9				HRS. WASHED					
LOAD on 7 cars					OHMS					
					CAKE CONDITION	6				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES 4 oz
DELIVER TO Hold for P E

SAMPLED BY

RELEASED BY

-DRYING-

Dry 20 Hrs at 200°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 4 oz
DELIVER TO Hold for P E

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 13
LUMP WGT. 2368
RELEASED BY B/L

-GRINDING-

MILL 8 HSP 1/8" RP SCREEN 3560 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 1 Pt Can
DELIVER TO CTL

DATE MIXED 7/29/80
SAMPLED BY 271

RELEASED BY

N37556.01

DUP050045782

35 85

51

18

1.28 +
0.14 -
2.06 +
0.14 -
1.28 +
0.14 -
1.22 +
0.14 -
1.23 +
0.14 -
1.23 +
0.14 -
2.00 +
0.14 -
1.22 +

0.14 -
2.07 +
0.14 -

1.21 +
0.14 -
1.25 +
0.14 -
2.01 +
0.14 -

22.03 *

1.79 +
0.14 -
22.03 +
23.03 *