

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A.J. Galuchie AT Piscataway DATE January 11, 1971
FROM H.R. Horton AT Burlington COPY TO H.B. Carr
SUBJECT Samples Submitted to Burlington Q.C.
by Mr. Matt Kubitsky ~~File~~

Reference: Memo A.J. Galuchie from H.R. Horton, 1/6/71

As noted in the referenced memo, Sample "A" was identified as an additive resin. Further analyses indicated that this sample was Type AR902.

The results are listed below along with the targeted ranges for this material.

	<u>"A"</u>	<u>Target</u>
Relative Viscosity	2.31	2.30-2.50
Volatiles	.12	0.6% max.
Brookfield (1 Day 20 rpm)	89	45-60
Severs (100 psig)	67	50-80
Hegman	7	4 min.


H.R. Horton

HRH/jt