

CG 03 CODE KY-787-D PKG.

JAN-9 33703

EST. WGT. 1090 LBS.

To Test

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (0)	ENK 9/22/76
	DCG 9/27/76
TYPED BY	
NE. 2/12/77	
MAKING NOTES	

REMARKS

Total WGT. 3490#

NAME: "KROLOR" YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	244					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-15-80					STARTED	10 AM				
TIME	5:00 PM					CAKES USED	46				
RELEASED BY	JAN					WATER ON	2 PM				
PRESS	22	23	24			HRS. WASHED	7				
NO. OF CAKES	46	46	52			OHMS	2000				
PRESS WITH						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD	on 6 cars					OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES 1-8oz JAR

DELIVER TO 6M for color

SAMPLED BY #376 RELEASED BY

-DRYING-

Dry 12 hrs at 220°F	LUMPL - OK - WET -	SALTS - CONTAMINATE
then dry 8 hrs at 160°F		

ADDITIONAL DRYING HOURS REQUIRED

No. Drums: 14

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT. 3587

RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 150 °F	MAX. TEMP.	°F

SCREEN	RPM
MAX. TEMP.	°F

EXPLAIN LOSSES

141105 20 ANE7

SAMPLE A / WITHOUT MIXING

SAMPLES 1 Env. & 1 Pt. can

DELIVER TO C.T.L.

DATE MIXED

SAMPLED BY

RELEASED BY

1 1

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE R 787 LOT 33678

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

1736	1		T- 71	
------	---	--	-------	--

1728	1		T 77	
------	---	--	------	--

STUMP

TOTAL NET WT. 3464 PKG. N-CODE _____

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

WJ 1/13/80