

ONE

GALLON

O'BRIEN'S

Flexico

MARINE TYPE SUPER ENAMEL

CHARTREUSE

FOR
INSIDE
OUTSIDE
USE

MANUFACTURED IN U.S.A. BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA

O'BRIEN'S FLEXICO ENAMEL

Made with Alki-therm, Flexico is a deluxe high-gloss enamel which imparts unusual beauty and extra protection to almost any surface. Popular for interior use in kitchens and bathrooms—on walls, trim, cabinets, furniture. Excellent for exterior work—on boats, porch furniture, etc. Its marine type formulation insures a tough, hard finish that's extremely resistant to water, sun, wear and abrasion. Easily applied with brush or spray. Flows on—no brush marks. Dries quickly.

DIRECTIONS FOR USE

NEW WOOD — apply one coat of O'Brien's White Surfacer or Double-Up Undercoat and finish with one or two coats of Flexico. Note—on boats use three thin coats of Flexico only. Thin first coat 10% with turpentine.

NEW PLASTER — apply one coat of O'Brien's Liquid Velvet Wall Primer and Sealer. Finish with one or two coats of Flexico.

NEW METAL—one coat of O'Brien's White Surfacer or Double-Up Undercoat followed with one or two coats of Flexico: Note—Use Tame-Rust Metal Primer on new steel boats. Galvanized or fiber glass boats require special primers and treatment.

OLD PAINTED SURFACES IN GOOD CONDITION —one or two coats of Flexico.

RECEIVED
REGD. NO. 15136
DATE 9-22-61

GENERAL DIRECTIONS —mix the enamel thoroughly before using and apply with a soft bristle brush. Sand and dust carefully between coats.

SURFACE PREPARATION — surfaces should be clean and dry, free of wax, oil, grease or soap compounds.

THINNING — Flexico is ready for use. If it appears too heavy and easier brushing is desired, thin accordingly with turpentine or O'Brien's Reducit.

DRYING—allow overnight drying between coats.

TINTING — Flexico Colors may be tinted with O'Brien's Tone-All Colors.

SAFE FOR BABY FURNITURE

LEAD FREE

DO NOT TAKE INTERNALLY CAUTION! COMBUSTIBLE

Keep away from heat and open flame. Keep out of reach of children. Avoid breathing of vapor or spray mist and prolonged contact with skin. Keep container closed when not in use. USE WITH ADEQUATE VENTILATION.

FLEXICO ENAMEL — TINT BASE
Pigment 20.31%
Triphenyl Oxide 55.15%
Triphenyl Oxide Pigment 100.00%
Vehicle 49.67%
Modified Phenolic Resin 3.00%
Aluminum Oxide 1.00%
Aluminum Oxide & Driers 100.00%
Less than 5% Tinting Colors Added.

THE O'BRIEN CORPORATION

SOUTH BEND, IND. BALTIMORE, MD.
OKLA. CITY, OKLA. SAN FRANCISCO, CAL.
LOS ANGELES, CAL.

ONE

GALLON

O'BRIEN'S

Flexico

MARINE TYPE SUPER ENAMEL

AQUA GREEN

FOR
INSIDE
OUTSIDE
USE

MANUFACTURED IN U.S.A. BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA

O'BRIEN'S FLEXICO ENAMEL

Made with Alki-therm, Flexico is a deluxe high-gloss enamel which imparts unusual beauty and extra protection to almost any surface. Popular for interior use in kitchens and bathrooms—on walls, trim, cabinets, furniture. Excellent for exterior work—on boats, porch furniture, etc. Its marine type formulation insures a tough, hard finish that's extremely resistant to water, sun, wear and abrasion. Easily applied with brush or spray. Flows on—no brush marks. Dries quickly.

DIRECTIONS FOR USE

NEW WOOD — apply one coat of O'Brien's White Surfacer or Double-Up Undercoat and finish with one or two coats of Flexico. Note—on boats use three thin coats of Flexico only. Thin first coat 10% with turpentine.

NEW PLASTER — apply one coat of O'Brien's Liquid Velvet Wall Primer and Sealer. Finish with one or two coats of Flexico.

NEW METAL—one coat of O'Brien's White Surfacer or Double-Up Undercoat followed with one or two coats of Flexico. Note—Use Tame-Rust Metal Primer on new steel boats. Galvanized or fiber glass boats require special primers and treatment.

OLD PAINTED SURFACES IN GOOD CONDITION —one or two coats of Flexico.

RECORDED
1519
DATE 4-22-61

GENERAL DIRECTIONS—mix the enamel thoroughly before using and apply with a soft bristle brush. Sand and dust carefully between coats.

SURFACE PREPARATION — surfaces should be clean and dry, free of wax, oil, grease or soap compounds.

THINNING — Flexico is ready for use. If it appears too heavy and easier brushing is desired, thin accordingly with turpentine or O'Brien's Reduct.

DRYING—allow overnight drying between coats.

TINTING — Flexico Colors may be tinted with O'Brien's Tone-All Colors.

SAFE FOR BABY FURNITURE

LEAD FREE

DO NOT TAKE INTERNALLY
CAUTION! COMBUSTIBLE

Keep away from heat and open flame. Keep out of reach of children. Avoid breathing of vapor or spray mist and prolonged contact with skin. Keep container closed when not in use. USE WITH ADEQUATE VENTILATION.

FLEXICO ENAMEL — TINT BASE
Titanium Dioxide 44.00%
Zinc Oxide 33.00%
Titanium Calcium Pigment 10.00%
Vehicle 13.00%
Keep Away From Heat
Keep Away From Children
Chloro Wood Oil Resin 3.75%
Aluminum Sprites & Driers 3.00%
Less than 5% Tinting Colors Added.

THE O'BRIEN CORPORATION

SOUTH BEND, IND. BALTIMORE, MD.
OKLA. CITY, OKLA. SAN FRANCISCO, CAL.
LOS ANGELES, CAL.