

Laboratory Report

Cyprus Industrial Minerals Co.
Research Division

2435 Military Avenue
West Los Angeles, California
Telephone (213) 478-0462

PLAINTIFF'S
EXHIBIT
CAM-343

Filing No 81-0237

References:

Key BEAVERHEAD 1982 DRILLING

Date of Report 11/11/82

Date of Work Request / By: O. Kortan

Copies:

R. S. Lamar
Exploration Dept.
T. Paul
A. Barth
B. Boudress

Reported By: P. Colville

Approved By: P. Colville *PC*

Classification:

Status: Complete: 4000 Series

Subject: Remaining Beaverhead drill cores have been analyzed for mineralogy.

Objective: The following holes have been analyzed. Mineralogy has been estimated by x-ray diffraction. High talc samples have been checked for LOI and GEB.

Holes: 4000, 4001, 4002, 4003, 4004, 4006, 4022, 4023, 4024, 4025, 4027, 4037, 4038, 4039, 4040, 4041, 4042, 4043, 4044, 4045, 4046, 4047, 4048, 4049, 4050, 4051, 4052, 4053, 4054, 4055, 4056, 4057, 4058, 4059, 4060, 4061, 4062, 4063, 4064, 4065, 4066, 4067, 4068, 4069, 4070, 4071, 4072, 4073.

The best talc seams are found in the following holes:
4023 (15 ft. seam), 4025 (15 ft.), 4027 (10 ft.), 4037 (5 ft., 15 ft.), 4038 (5 ft. & 5 ft.), 4047 (15 ft.), 4048 (10 ft.), 4060 (15 ft), 4061 (5 ft.). Hole 4054 has a lot of talc, nearly 70 ft. of 75% or better, but the talc is discolored.

P. Colville
P. Colville

PC:es
Attachments

CYPRUS

ITA-Ratcliff-000125