Rad 2

GEORGIA-PACIFIC

INTERDEPARTMENTAL COMMUNICATION

DATE: September 21, 1971

TO: Mr. J. B. Moss — LOCATION: Tigard

FROM: L. E. Winter — LOCATION: Acme

SUBJECT: Supplement to Correspondence Dated August 31, 1971
Comparison of All Purpose Compounds

PLAINTIFF'S EXHIBIT
GP-774

RECEIVED
SEP 24 1971
TECHNICAL DEPARTMENT

PACO

WC	62
PH	9.0
Bond	100%
Workability	Good
Shear	OK
Shrinkage	Poor
Edge Crack	Good
Wedge Crack	Fair
Hardness	OK
Adhesive	Starch
Viscosity	500
Working Time	20 min.

We rated the Paco the same as U.S.G., which was No. 5 on the comparison conducted August 31, 1971.

L. E. W.

LEW/om

cc: Messrs. T. W. Richards
C. W. Lehnert
D. C. Corkill
W. N. Gettel
K. W. Brown
D. M. Watson
E. E. Schram

THIS COPY FOR