

CODE <u>Hy 795</u>		LOT <u>35617</u>		
NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
<u>2200</u>	<u>1</u>	<u>T-173</u>		
<u>2155</u>	<u>1</u>	<u>T-246</u>		
STUMP <u>Lump 4,404</u>				
TOTAL NET WT. <u>4,355</u>		PKG. N-CODE		
PROD. SPVR. <u>JV</u>		DATE <u>5/8/80</u>	WHSE. OPER.	

CG	03	CODE	KY-795-D	PKG.
			35617	
EST. WGT.		1178	880	LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-795-D (I)	EWK 10/6/76
Alternate	DCG 10/7/76
TYPED BY	
NE 3/3/77	

MAKING NOTES

REMARKS

Total Wgt: 4878#

NAME: "KROLOR" YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT	243					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-5-80					STARTED	10:25 AM				
TIME	9:30 PM					CAKES USED	46				
RELEASED BY	<i>[Signature]</i>					WATER ON	2:30 PM				
PRESS	22	23	24	24		HRS. WASHED	10				
NO. OF CAKES	46	46	46	52		OHMS	5000				
PRESS with						HRS. WASHED					
WASH TO	5000					OHMS					
TEST AFTER	5					HRS. WASHED					
LOAD	on 5 cars					OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO CFI for color

SAMPLED BY *[Signature]*

RELEASED BY

-DRYING-

Dry 16 Hrs. at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

**SAMPLES
DELIVER TO**

NO. CARS PULLED	
SAMPLED BY	

No Drums : 14

LUMP WGT. 4404
RELEASED BY SPK

—GRINDING—

MILL 939 HSP 3/32" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 210 °F		MAX. TEMP.	° F
		EXPLAIN LOSSES	
SAMPLE WITHOUT MIXING		DATE MIXED	
SAMPLES 1 Env & 1 Pt Cap		SAMPLED BY	RELEASED BY
DELIVER TO CTL			

DUP050456443

N32066.01

3 5 6.17 N (
4 1.00 N
1.58 N
.00 T

3.19 (
.12 -
3.30
.12 -
3.23
.12 -
3.35
.12 -
3.30
.12 -
3.34
.12 -
3.25
.12 -
3.44
.12 -
3.22
.12 -
3.34
.12 -
3.37
.12 -
3.28
.12 -
3.47
.12 -
2.64
.12 -
4 4.04 T

DUP050456444

N32066.02