

CG 01 CODE YE-698-D PKG

LOT **E1099**

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 92 93
NO. OF CAKES 54 54 54
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED 1+4
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP - OK - WET - SALTS - CONTAMINATED

Color appears dry.
ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 20
LUMP WGT 5754
Joe

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

RPM SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

YE 698

1099
41
56

0.00 *

0.00 *

3.11 +
0.12 -/
3.24 +
0.12 -/
3.14 +
0.12 -/
3.00 +
0.12 -/
2.93 +
0.12 -/
2.95 +
0.12 -/
3.05 +
0.12 -/
3.01 +
0.12 -/
3.22 +
0.12 -/
3.06 +
0.12 -/
2.96 +
0.12 -/
2.99 +
0.12 -/
2.95 +
0.12 -/
3.10 +
0.12 -/
3.04 +
0.12 -/
2.95 +
0.12 -/
46.78 *

1099
41
124

0.00 *

3.53 +
0.14 -/
3.44 +
0.14 -/
3.25 +
0.14 -/
1.10 +
0.14 -/
10.76 *

46.78

57.54