RAW MATERIAL BULLETIN DRYWALL ACCESSORY PRODUCTS	ASBESTOS 7RF10	BULLETIN NO: DATE: PAGE:	RM-J045 6/20/72 1 of 1
APPROVALS:		CANCELS: DATE:	RM-J045 12/4/69

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

PLAINTIFF'S EXHIBIT

KG-228

SPECIFICATIONS:

1.	Mixing Water Requirement	480 to 550
2.	Free moisture (200°F)	2.0%
3.	Color	Light Gray
4.	Grit	0.05% maximum. All passing 80 mesh screen
5.	Calcium carbonate (CO_2 method)	1.0% maximum
6.	Canadian screen	0.0-0.0-0.0-16.0
7.	pH (10% dispersion)	7-8
8.	Wet bulking	250-350

PLAINT
EXHI
HOB
11-4

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching a

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."

RAW MATERIAL BUL'E.. DRYWALL ACCES. RY PRODUCTS	ASBESTOS 7RF9	LETIN NO: RM-J046 DATE: 6/20/72 PAGE: 1 of 1
APPROVALS:		CANCELS: RM-J046 DATE: 12/9/69

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

SPECIFICATIONS:

1.	Mixing Water Requirement	450 to 550
2.	Free moisture (200°F)	2.0%
3.	Color	Light Gray
4.	Grit	0.05% maximum. All passing 80 mesh screen
5.	Calcium carbonate (CO_2 method)	1.0% maximum
6.	Canadian screen	0.0-0.0-0.0-16.0
7.	pH (10% dispersion)	7-8
8.	Wet bulking	200-300

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asbe

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."

RAW MATERIAL BULLETIN DRYWALL ACCESSORY PRODUCTS	ASBESTOS 7TF1	BULLETIN NO: RM-J050 DATE: 6/20/72 PAGE: 1 of 1
APPROVALS:		CANCELS: RM-J050 DATE: 1/26/71

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

SPECIFICATIONS:

1.	Mixing Water Requirement	330 to 370
2.	Free moisture (200°F)	2.0% maximum
3.	Color	Light Gray
4.	Grit	0.05% maximum. All passing 80 mesh screen
5.	Calcium carbonate (CO_2 method)	1.0% maximum
6.	Canadian screen	0.0-0.0-0.0-16.0
7.	pH (10% dispersion)	7.5-8.5
8.	Wet bulking	100-130

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asb

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."