

cc: E. J. O'Brien
J. E. McCarty
E. Bonet
R. K. Hoagland
H. Forist
E. C. Lindstrom, DEQ
E. Bauman
File (2)
E/S (1)

JOHNS-MANVILLE
CONTROL LABORATORY
MANVILLE GENERAL PLANT

Report: 33-154
Date: 6-6-57

PLAINTIFF'S
EXHIBIT
CSR-505

Subject: Blended Blue Crocidolite Asbestos Fibre - 440 bags
Requested by: R. K. Hoagland
Identification: Received 5/27/57 from the Asbestos Corporation of America
Order #M-6177 - Req. C-141

SUMMARY:-

The samples tested of the shipment of 440 bags received on 5/27/57 passed
Purchase Specification II-1983-1.

DATA:-

McNett Test Method TX 10.15 - Percent

<u>Sample</u>	<u>1</u>	<u>2</u>	<u>Average</u>	<u>P.S. II-1983-1</u>	
				<u>Min.</u>	<u>Max.</u>
+14 Mesh - Fibre & Rock	36.4	34.4	35.4	0	2
+14 Mesh - Rock	----	----	----	0	2
+14 Mesh - Fibre	36.4	34.4	35.4	30	50
+28 Mesh	5.5	4.6	5.1	0	13
+100 Mesh	8.0	7.7	7.8	0	16
Cum. +100 Mesh	49.9	46.7	48.3	--	--
+200 Mesh	7.1	8.2	7.7	0	16
-200 Mesh	43.0	45.1	44.0	36	56

cjp

APPROVED: R. Jacobs

REPORT BY: W. Easterha

002271

PLAINTIFF'S
EXHIBIT

108560