

VISCOSITY WORK SHEET

Item	2647 2662	P.T.No.	Date	3-18-55	
Worker	L. KAY	Polymer	MMA Lucite	Solvent	EDC
For	GRAF Wolfe	Charge	1290	Temperature	25°C.
Viscometer No.	I	Efflux Time	221.4	Weight:	Gross 5.1979
Viscometer No.	2	Efflux Time	219.8		Tare 5.0729
Viscometer No.	III	Efflux Time	248.1		Net 0.1250
	A		2885		

Net 0.1250/2500

0.5000 / 10000

	Sample	Flask No.	Visc.	Solution Efflux Times	Rel. Inh. Visc.	Visc. or M.W.
4296-115-B7G	13	I		276.9; 277.2; 277.1	1252	107,500 ✓
	14	2		275.9; 275.9	1254	108,500
#1 Sample 5787-ppt	TC	III		395.9; 395.9	1593	325,000
	EC	A		462.4; 462.2; 462.2	1596	327,000
5787	TD	I		575.1; 575.2; 575.1	2.601	1,050,000
	L10	2		569.9; 570.1; 570.2	2.600	1,050,000
				Underlined or gell visible	5787	
				Used fritted filters	5787	Sample

Undersized on #20 mesh	5787	
Used fitted filters	5787	Sample

PC-1

N38652