



PRODUCT DATA

PLAINTIFF'S

EXHIBIT NO. 2-15
FOR IDENTIFICATION

DATE: 3/29/78 RPT: BT

1615 AGI TALC (B.C.)*

Typical Chemical Analysis:

		Percent
Silica	SiO ₂	58-62
Calcium Oxide	CaO	0.6-1.2
Aluminum Oxide	Al ₂ O ₃	2-4
Magnesium Oxide	MgO	29-31
Moisture	not more than	0.5
Loss on Ignition	not more than	7
Water Solubles	not more than	0.1
Acid Solubles	not more than	6
Water Soluble Iron		None
pH		9-10

Typical Physical Properties:

Dry Brightness	85-90
Specific Gravity	2.68
Tapped Density, lbs./cu.ft.	56-60
Loose Density, lbs./cu.ft.	24-29
Lbs./solid gallon	22.32
One Lb. Bults, gallons	0.0448
Oil Absorption	28-32
Thru 200 mesh, %	98

Typical Particle Size Distribution:

Microns	% Less Than	Microns	% Less Than
40	90	5	5
30	76	4	3
20	50	2	1
10	16		

*Bacteria Controlled, CTPA, "Microbiological Control Guidelines for Cosmetic and Toiletries, 1973." Combined count of less than 500 microorganisms per gram and the absence of gram negative bacteria.

J110

PLAINTIFF'S
EXHIBIT
WCD-288