cc: J. B. McCarty
S. Bonet
R. A. Scharmann (2)
E. Ponisi
E. C. Lindstrom, CHQ
J. Collopy
File (2)
B/F (1)

JOHNS-MANVILLE
CONTROL LABORATORY
MANVILLE GENERAL PLANT

Report: CC-14196
Date: 11-14-56

PLAINTIFF'S EXHIBIT
OSR-501

Subject: Blended Blue Asbestos Fibre for 63 Sheet Packing
Requested by: R. A. Scharmann
Identification: 500 Bags received 11/6 and 532 Bags received 11/8/56
From - Asbestos Corporation of America on Req. C-503

DESCRIPTION:-

Two samples were taken from each truck shipment, each sample a composite of five (5) bags.

SUMMARY:-

McNett Screen Tests show that these two shipments pass P.S. 61925-1. The average of the +14 Mesh fibre is 33.8%, the Minimum requirement of the purchase specification is 30%.

DATA:-

McNett Screen Test

Shipment Dates	11/6/56		11/8/56			P.S. 61925-1	
Sample Number	1	2	1	2	Avg.	Min.	Max.
+14 M Fibre & Rock	30.8	33.8	35.3	35.4	33.8	30%	50%
+14 M Rock	----	----	----	----	----	----	2%
+14 M Fibre	30.8	33.8	35.3	35.4	33.8	----	----
+28 M	4.6	4.4	3.6	3.6	4.0	0	13%
+100 M	6.5	6.4	6.0	6.2	6.2	0	16%
Cum. +100 M	41.9	44.6	44.9	45.2	44.0	----	----
+200 M	6.0	5.8	5.6	5.5	5.7	0	10%
-200 M	52.1	49.6	49.5	49.3	50.3	36%	56%

cjz

APPROVED: R. Jacobs

REPORT BY: W. J. Westerman

PLAINTIFF'S EXHIBIT
10852.0