

FOSECO, INC.

INTER-COMPANY AND INTER-DEPARTMENTAL CORRESPONDENCE



TO: M. Wood


FROM: A. G. Santighian

DATE: October 25, 1973

SUBJECT:

As was established during Thursday's, October 18, 1973, meeting, I forward to you the necessary machine and equipment modifications due to non-asbestos non-paper recipes which in short time should be used under regular basis in production.

- 1) Each blow tank should be modified similar to Chicago's blow tanks or, after a fair trial, similar to K-4.
- 2) The holding tanks need baffles more prominent than they have and the mixing blade should be in a frame form. Also, the mixing blade speed should be between 20-24 rpm's.
- 3) Before any other work is done on the prebatch station, another experiment should be made in Mt. Braddock to obtain a Premix-Profax 31 or Premix-EP5465 batch and then should be analyzed by our lab for density, transverse strength and loss on ignition. Meantime, it should be tried under regular conditions in production by using it on different machines. The boards and/or tops obtained should be analyzed by our lab and Quality Control Lab.


A. G. Santighian

AGS/cel

Cc: W. J. Vandemark
H. D. Shephard
P. A. Partington
W. C. Fletcher