FORMULA RECORD

Goods Glidden Endurance White Paint (Semi-Paste) Formula Y-502

Consistency Date 12-15-1920 Old No.

For Use on Classification

1	5	½ Bbl	Bbl.	2 Bbl.	Code No.	Per cent	Manufacturing Specifications
1 1/2	Gal.	Raw Linseed Oil			O-1		Grind
1 1/2	"	Acid Refined Linseed			O-2		Kind of Mill
1/2	"	Blown Soya Bean Oil			O-61		Rate per hr.
1	"	Texaco			S-43		Strainer
1/2	"	W.E.Drier			D-15		
50	lbs.	Standard Zinc			W-5		Analysis
80	"	Sublimed Lead			W-1		
50	"	Silica			W-16		
10	"	Pulp			W-11		
3/4	ozs.	P-2-E Blue			B6-5		

discontinued
see Y502A

N12099

GLD059838

FORMULA RECORD

Goods Glidden Endurance White Paint (Semi Paste Formula No. Y-502-A

Consistency Date 11-9-26 Old No.

For Use on Cost Classification

1	5	½ Bbl.	Bbl.	2 Bbl.	Code No.	Per cent.	Manufacturing Specifications
20	gal.	Alkali Refined Linseed			O-52		Grind
10	"	Acid Refined Linseed			O-2		Kind of Mill
2	"	Texaco			S-43		Rate per hr.
8	"	B-Magic Drier			D-7		Strainer
400	lbs.	Special Sunolith			W-77		Weight per Gallon
360	"	No. 550 Zinc			W-90		Light Baume Temp.
300	"	Barytes			W-10		Heavy Baume Temp.
40	"	Pulp			W-11		Viscosity Temp.
							Make of Viscosimeter
							Flash Point
							Is Agitator Package Required
							Remarks
							Discontinued
							2-27-28
Yield							

GLD059840

Pigment	78.5%	
Liquid	21.5	
	100.0%	
Pigment:		
Lithopone		36.4%
Zinc Oxide		32.8
Barium Sulphate		27.3
Silica & Silicates		3.5
		100.0%
Liquid:		
Vegetable Oil		77.4%
Mineral Spirits		4.3
Liquid Drier		18.3
		100.0%

Weight per gal. 19.6 lbs.

Steel Pails 5s.

Round Cans 1s, 1/2s, 1/4s.

"Enduratex White - Semi Pas" Labels.

GLD059841

λ-480-D .50M 3-55.

FORMULA RECORD

Goods End. Semi Paste White — Formula No. 9502

Consistency Semi Paste — Date 5/6/35 — Laboratory No.

For Use on — Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
0132	6½			26						Grind
27	1¼			5						Kind of Mill
514	¼			1						Strainer
										Weight per Gallon
W69		11	4		360					Light Baume Temp.
W6		11	4		360					Heavy Baume Temp.
W10		6			192					Viscosity Temp.
W11		1	8		48					Viscosimeter
										Flash Point
										Is Agitator Required
										Remarks
										9 lbs
										Absent Minded
										Use 9502 C
Yields										

GLD059842

420-S 50M 7-37 (2)

FORMULA RECORD

Goods Endurance Semi Paste White Formula No. 9502C

Consistency S. Paste Date 10-8-37 Laboratory No. 0

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
0152	4						16			Grind C
05	2½						10			Kind of Mill Stone
D7	1¼						5			20-21 #
814	¼						1			Weight per Gallon
										Light Baume Temp.
W69		11	4					360		Heavy Baume. Temp.
W6		11	4					360		Viscosity Temp.
W10		6						192		Viscosimeter
W11		1	8					48		Flash Point
										Is Agitator Required
										Remarks JPW
						DISCONTINUED				
						SEE				
Yield										

GLD059843

4M-D 3CM 11-41. PRINTED IN U.S.A. (B)

FORMULA RECORD

DISCONTINUED

Goods Conductance Semi Paste White. Formula No. Y502

Consistency Semi Paste. Date 2/18/42 Laboratory No. 1

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
01	5¼						21			Grind C
064	½	Standard Formula					2			Kind of Mill
D15	1	Not to be taken					4			Strainer
543	1	from File					4			Weight per Gallon 19.5
514	¼						1			Light Baume Temp.
										Heavy Baume Temp.
W6		10						320		Viscosity Temp.
W95		10						320		Viscosimeter
W16		6						192		Finish Point
W17		4						128		Is Agitator Required
										Remarks
	Replaces Card Dated 1-30-42									JPW
										Y502E
	Revised to show improved analysis									
	Canceled 7-7-44									
Yield										

GLD059844

484-D 50M PRINTED IN U.S.A. (8)

FORMULA RECORD

Goods Endurance S. Paste White — Formula No. 1502-F

Consistency S. Paste — Date 2/17/44 — Laboratory No. 1

For Use on — Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specificatio
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
011	5½			22						Grind C
064	½			2						Kind of Mill
815	1			4						Strainer
543	¾			3						Weight per Gallon 20#
514	¼			1						Light Baume Temp.
										Heavy Baume Temp.
W6		11	4		360					Viscosity Temp.
W69		11	4		360					Viscosimeter
W10		4	11		150					Flash Point
W11		3	2		100					Is Agitator Required
										Remarks
										QPW
										3.25# oil/GAL
Yield										

Standard Formula
Not to be taken
from File.

GLD059845

400-D 5M 4-41 PRINTED IN U.S.A. (WPI)

FORMULA RECORD

Goods Endurance S. Paste White. Formula No. V502E

Consistency S. Paste Date 2/17/44 Laboratory No. 1

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specification
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
011	5½			22						Grind C
064	½			2						Kind of Mill
815	1			4						Strainer
543	¾			3						Weight per Gallon 20#
514	¼			1						Light Baume Temp.
										Heavy Baume Temp.
016		1	4		360					Viscosity Temp.
069		1	4		360					Viscosimeter
010		4	0		1440					Flash Point
011		3	2		100					Is Agitator Required
										Remarks
						DISCONTINUED 4/13/44 PD				
						SEE V502F				3.25 Tint/Gal

GLD059846

460-D 5M-11-35

FORMULA RECORD

Goods Endurance A Paste White Formula No. Y502E

Consistency A Paste Date 2/17/44 Laboratory No.

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
O-1	5½									Grind C
O-64	½									Kind of Mill
O-15	1									Strainer
S-43	3/4									Weight per Gallon 20#
S-14	¼									Light Baume Temp.
										Heavy Baume Temp.
W-6		11	4							Viscosity Temp.
W-69		11	4							Viscosimeter
W-10		4	11							Flash Point
W-11		3	2							Is Agitator Required
										Remarks
				Standard Formula. Not to be taken from File.						
Yield										

GLD059847

ABC-A

FORMULA RECORD

Goods Endurance Semi-Paste White — Formula No. Y-502 F

Consistency — Date 10-31-47 — Laboratory No.

For Use On — Cost Classification

CODE NUMBER	ONE GALLON BATCH GALS.	LBS.	OZS.	100 GALLON BATCH GALS.	LBS.	OZS.	GALS.	GALLON BATCH LBS.	OZS.	MANUFACTURING SPECIFICATION
Y-2 (c)					300					GRIND
Y-36					500					KIND OF MILL Stone/Hy R
Y-119					775					STRAINER
Y-10					325					WEIGHT PER GALLON 25
Y-11					215					LIGHT BAUME TEMP.
										HEAVY BAUME TEMP.
O-1				17						VISCOSITY Heavy TEMP.
O-63				16						VISCOSIMETER
D-15				7						FLASH POINT
S-43				8						IS AGITATOR REQUIRED
S-48				3						REMARKS
S-14				1.5						Standardized.
										R.G.
YIELD										

Formula Not to be taken from File

GLD059848

46-O 50M - 1-45 PRINTED IN U.S.A. (E)

FORMULA RECORD

Goods Exterminator Special Lacquer Thinner Formula No. 4502F

Consistency Liquid Date 4-13-46 Laboratory No.

For Use on Cost Classification

Code Number	One Gallon Batch Pints.	Lbs.	Ozs.	Gallon Batch Gals.	Lbs.	Ozs.	Gallon Batch Gals.	Lbs.	Ozs.	Manufacturing Specification
4476		11	4		360			720		Grind 3.
4467		11	4		360			720		Kind of Mill Steel Mill
4610		4	11		150			375		Strainer 80 Mesh
4611		3	2		100			250		Weight per Gallon
										Light Baume Temp.
A 286	2 3/4			11			27½			Heavy Baume Temp.
A 1	3 3/4			9½			23¾			Viscosity Temp.
2-45	1			4			10			Viscosimeter
5-93	1 3/4			4 3/4			11¾			Flash Point
5-92	½			2			5			Is Agitator Required
5-10	¼			1			2½			Remarks
										H.E.H.
										DISCONTINUED
										SEE 4502H
										12/13/46
Yield										

Standard Formula Not to be taken from File

GLD059849

Characteristics and Method of Using	Cost Data				Customers
Type of Goods Leather Finish					
Color White					
Luster					
Match for					
Kind of Reducer Water					
Amount of Reduction for 1:1					
Brushing ✓					
Spraying Pressure					
Dipping Drip Time	Analysis				
Flocoing Drip Time	Pigment 79.9 %				
Tumbling	Vehicle 20.1 %				All plants 4-25-46
Air dry to recoat 72 hours	100.0 %				
To Sand or Rub	Pigment				
Bake Time Temp.	35% Ferbend 2 Iron Oxide				51.4 %
Rub with	Titanium				3.1 %
Polish with	Titanox Extender				25.5 %
Schedule	Magnesium Silicate				19.9 %
					100.0 %
	Vehicle				
	Linseed Oil				46.05 %
	Linseed Soya				18.40 %
	Soya Oil				12.10 %
	Driers				3.45 %
					100.00 %

GLD059850

480-D 50M 10-48 PRINTED IN U.S.A. (B)

FORMULA RECORD

Gloss Endurance Semi Paste White Formula No. Y502-B

Consistency S. Paste Date 12-13-46 Laboratory No.

For Use on Cost Classification

Code Number	One Gallon Batch			63 Gallon Batch			Gallon Batch			Manufacturing Specification
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
W-6		11	4		360			900		Grind 2
W-69		11	4		360			900		Kind of Mill Stone
W-10		4	4		150			375		Strainer Hi-R
W-11		3	2		100			250		Weight per Gallon
										Light Baume Temp.
O-286	2 3/4			11			27 1/2			Heavy Baume Temp.
O-5	2 5/16			9 1/4			23 1/8			Viscosity Hoe Temp.
D15	1 3/16			4 3/4			11 7/8			Viscosimeter
S-43	1			4			10			Flash Point
S-78	1/2			2			5			Is Agitator Required
S-14	1/4			1			2 1/2			Remarks H.G.H
	Changed to use O-5									
								DISCONTINUED		
			Standard Formula. Not to be taken from File.					SEE		
Yield										

GLD059851

Characteristics and Method of Using		Cost Data			Customers
Type of Goods	Paste Paint				
Color	White				
Luster					
Match for					
Kind of Reducer	Oil	Pigment		79.9%	
Amount of Reduction for	1:1	Vehicle		20.1%	
Brushing				100.0%	All plants 1-8-47
Spraying	Pressure				Wagner-Reding 6/1/48
Dipping	Drip Time	Pigment Analysis			Atlanta (KHH
Flocoing	Drip Time	35% Leaded Zinc Oxide		37.1%	3-10-53
Tumbling		Lithopone		37.1	
Air dry to recoat	72 hours	Barium Sulphate		15.5	Buena P.I.P.
To Sand or Rub		Magnesium Silicate		10.3	9-5-50
Bake Time	Temp.			100.0%	
Rub with		Vehicle			
Polish with		Linseed Oil		66.85%	
Schedule		Mineral Spirits		18.40	
		Liquid Drier		12.18	
		Water		2.45	
				100.00%	

GLD059852