

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

4/22/82

CG 01 CODE YE-698-D PKG

PROCESSES APPROVED BY
YE-698-D (S) F. POST 10/09/81
ALTERNATE
TYPED BY JMH

LOT

F2H06

MAY 25 1982

EST. WT. 5547* LBS.

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT	245	8			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-15				STARTED	9:00 AM				
TIME	8:00 AM				CAKES USED	54				
RELEASED BY	JMH				WATER ON	11:00 AM				
PRESS	2	92	93		HRS. WASHED	3				
NO. OF CAKES	54	54	54		M MHOS	50				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER					M MHOS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD ON 7 CARS					M MHOS					
					CAKE CONDITION					
					NO CARS LOADED	7				
					EXPLAIN LOSSES					
					2 Bleeds Catching into Box					

SAMPLES 8 OZ
DELIVER TO CTL.SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

NO CARS PULLED

NO DRUMS 21

DELIVER

SAMPLED BY

LUMP WGT 6035

RELEASED BY A2

CO-GROUND PER CTL INSTRUCTIONS

GRINDING

MILL MIKROATOMIZE SCREEN

RPM

SCREEN

RPM

MAX. TEMP DEG F

MAX. TEMP.

F

SET ROOF BLAST - GATE AT 9" FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE

DATE MIXED

SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTLSAMPLED BY
RELEASED BY

N39443

1

5565