



ASBESTOS TESTING INC.

5205 NOYES AVE. • CHARLESTON, WV 25304 • (304) 925-6795

February 2, 1987

Mr. Erik Osby
Rhone-Poulenc
Union Carbide Agricultural Products
Industrial Hygiene Dept.
P.O. Box 2831
Charleston, WV 25380

The following bulk insulation analysis results pertain to twenty-two insulation samples received on 1/29/87. All bulk samples are analyzed in accordance with EPA recommendations concerning the analysis of bulk materials for asbestos using Polarized Light Microscopy.

ANALYSIS RESULTS

Sample #1

Tank 4552	40%-Asbestos (Chrystile) 60%-Clay
-----------	--------------------------------------

Sample #2

LP Cond. Tank 6392-2150	80%-Asbestos (5%-Amosite) (75%-Chrysotile) 20%-Clay
-------------------------	---

Sample #3

East TSS Calandria, 6376-29652	N.D.-Asbestos 10%-Mineral Wool 90%-Perlite
--------------------------------	--

Sample #4

Tank 4550 & 51	80%-Asbestos (75%-Chrysotile) (5%-Amosite) 20%-Clay
----------------	---

Sample #5

TRC FD/TS HXER, 6376-559	N.D.-Asbestos 40%-Cellulose 60%-Clay
--------------------------	--

Sample #6

4548 Tank, 6392-2186

N.D.-Asbestos
15%-Mineral Wool
85%-Perlite

Sample #7

4546 Tank, 6392-2091

N.D.-Asbestos
40%-Cellulose
60%-Clay

Sample #8

TRFS VEnt Condensor, 6392-2091

N.D.-Asbestos
70%-Cellulose
30%-Clay

Sample #9

4527 Tank, 6392-2095

65%-Asbestos
(5%-Amosite)
(60%-Chrysotile)
35%-Clay

Sample #10

4545 Tank, 6392-2393

65%-Asbestos
(5%-Amosite)
(60%-Chrysotile)
35%-Clay

Sample #11

1976 East TSS Calandria,
6376-29651

N.D.-Asbestos
5%-Mineral Wool
95%-Perlite

Sample #12

4502 Tank

45%-Asbestos
(5%-Amosite)
(40%-Chrysotile)
55%-Clay

Sample #13

TRS OVHD Pot, 6476-26506

N.D.-Asbestos
20%-Mineral Wool
80%-Perlite

Sample #14

Mobil Therm Calandria,
6376-1983

N.D.-Asbestos
40%-Cellulose
60%-Clay

Sample #15

Tone Ref. OVHD Pot 6392-2171

N.D.-Asbestos
40%-Cellulose
60%-Clay

Sample #16

TSS Overhead Pot, 6395-519

55%-Asbestos
(15%-Amosite)
(40%-Chrysotile)

Sample #17

Mobil Therm Calandria, 6376-1184

N.D.-Asbestos
10%-Mineral Wool
90%-Perlite

Sample #18

Evap. Cond. Pot, 6392-2172

65%-Asbestos
(5%-Amosite)
(60%-Chrysotile)
35%-Clay

Sample #19

Evap., 6376-0008

60%-Asbestos
(20%-Amosite)
(40%-Chrysotile)
40%-Clay

Sample #20

Tin Rec. OVHD Pot, 6395-567

60%-Asbestos
(20%-Amosite)
(40%-Chrysotile)
40%-Clay

Sample #21

4549 Tank, 6392-2185

60%-Asbestos
 (20%-Amosite)
 (40%-Chrysotile)
40%-Clay

Sample #22

H.P. Cond. Tank, 6392-2149

30%-Asbestos (Chrysotile)
70%-Clay

Respectfully submitted,

John S. Ferrell
Industrial Hygienist