

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A. Stasenko AT Burl. Compound DATE August 26, 1969
 FROM E. L. Kanyok AT Burlington COPY TO H. B. Carr
 SUBJECT Firestone 225 Resin H. H. Duhamel
 P. Gawason
 P. R. Scarito
 File ✓

The results of Firestone 225 resin received on 8/22/69 and 8/25/69 are as follows:

<u>Properties</u>	<u>8/22/69</u>	<u>8/25/69</u>	<u>Burlington 225 Spec.</u>
Relative Viscosity	2.29	2.32	2.26 - 2.33
Gels	8	11	13 maximum
Dry Blend	6.4	6.3	6.0 - 8.0
Screen			
+40	-	-	-
+60	1	2	0-Tr
+80	32	47	-
+100	71	77	40 - 70
+140	94	95	-
+200	99	100	-
Thru	1	-	0-5

E. L. Kanyok
 E. L. Kanyok

ELK/rjl