CG 40 CODE RT-160-P PKG. 04

→ JAN 28 81 38837

EST. WGT. 665 LBS.

2 24

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-160-P (C)	BBK 04-26-77
	OCG 04-26-77
	BBK 03-22-79
TYPED BY	
emw032679	

MAKING NOTES

REMARKS

NAME: NAPHTHANIL® RED LIGHT

NON-BLEEDING

INSTRUCTIONS						-PRESSING- RECORD					
VAT	260					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-28-81	EM				STARTED	6:30 pm				
TIME	5:45 P					CAKES USED	36				
RELEASED BY	EH					WATER ON	11:30 pm				
PRESS	12	26				HRS. WASHED	5 1/2				
NO. OF CAKES	36	40				OHMS	5000				
PRESS without AGITATION						HRS. WASHED					
WASH TO 4000 OHMS with 35-75°F water						OHMS					
TEST AFTER 2 HOURS						HRS. WASHED					
LOAD in N-1775-A at 360# net per drum						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					

EH

THIEF } 1 Pt for CTL &
SAMPLES } 1 Qt for Pre-Shipment
DELIVER TO CTL

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

HOURS	L.V.	H.V.	LUMP: - OK - WET - SALTS - CONTAMINATE
DO NOT DRY			ADDITIONAL DRYING HOURS REQUIRED
SAMPLES			NO. CARS PULLED / LUMP WGT.
DELIVER TO			SAMPLED BY / RELEASED BY

-GRINDING-

MILL	SCREEN	RPM	SCREEN	RPM
MAX. TEMP.	°F		MAX. TEMP.	°F
DO NOT GRIND				
SAMPLE AFTER / WITHOUT MIXING			DATE MIXED	
SAMPLES				