Mr. O'Neal 7/11/40

AROCLOR 1254

Resistivity results on last 10 lots are shown below:

| Lot No. | Resistivity | do. aged 96 hours |
|---|---|---|
| 31 | 1060 | 1425 |
| 30 | 1020 | 935 |
| 29 | 980 | 1140 |
| 28 | 670 | 550 |
| 27 | 1060 | 900 |
| 26 | 740 | 815 |
| 25 | 635 | 790 |
| 24 | 435 | 890 |
| 23 | 1790 | 1330 |
| 22 | 1480 | 1220 |
| Avg. | 990 | 1000 |

The above indicates that little change is caused by aging. The differences found are probably within the experimental error of the measurement.

Specification calls for a minimum of 100 (x $10^9$) with no drop on aging.

P Gerber

DSW 331080

STLCOPCB4077724