

NOV 5 1982

L2H92

PROCESS
KO-906-D (C)APPROVED BY:
FWP 06/14/82

*DATE

LOT NUMBER

MAKING NOTES _____

EST. WT. 5006* LBS.

JOB NAME: 04KO906DFC

INSTRUCTIONS

PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 22 23 24 25
NO. OF CAKES 46 46 52 48
PRESS WITH AGITATION
WASH TO 2000 OHMS - 135-145 F WATER
TEST AFTER 3 HOURS
LOAD ON 6 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F

NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 8 OZ. JAR
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 16
5215

= GRINDING =

MILL 939 HSP 3/32"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN
MAX. TEMP. F

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTL

EXPLAIN LOSSES
EXPLAIN LOSSES
DATE MIXED
SAMPLED BY
RELEASED BY

92
41
16

0.00 *
3.63 +
0.12 -
3.45 +
0.12 -
3.26 +
0.12 -
3.35 +
0.12 -
3.16 +
0.12 -
3.15 +
0.12 -
3.32 +
0.12 -
3.43 +
0.12 -
3.57 +
0.12 -
3.25 +
0.12 -
3.39 +
0.12 -
3.48 +
0.12 -
3.44 +
0.12 -
3.34 +
0.12 -
3.55 +
0.12 -
3.30 +
0.12 -
52.15 *

R