



INTERNAL CORRESPONDENCE

RECEIVED

UC 149-2

AUG 08 1974

R. N. WHEELER, JR.

CHEMICALS AND PLASTICS

P. O. BOX 471, TEXAS CITY, TEXAS 77560

TO (NAME) Mr. M. E. Eisenhower
COMPANY
LOCATION TEXAS CITY PLANT

DATE August 5, 1974

COPY TO Dr. W. B. Ackart - 312
Dr. C. E. Colwell - 525
Mr. R. L. Frantz
Mr. R. E. Graebert - 511
Mr. R. J. Hanna - 511
Mr. F. L. Johnson
Mr. R. W. Sesler
Mr. G. T. Scott - 501
Dr. A. B. Steele - 501
Mr. G. F. Tacquard
Mr. R. N. Wheeler
Dr. N. L. Zutty - 501

SUBJECT Residual VCM Content of
Suspension Vinyl Resins

Attached in Table I is a summary of the VCM content of the suspension vinyl resins produced during July, 1974. The data continue to confirm that the continuous stripping of suspension resins since May has resulted in an overall reduction in the residual VCM content of all resin types. Some inconsistencies in the stripping/drying area continue to be observed, particularly with QSAN-7. A detailed tabulation of the resins produced during July is provided in Tables II - V.

RMA/sn
R. M. Arnold

RMA/sn

Attachment

UCC
061295

TABLE I
REVIEW OF VCM DATA OF SUSPENSION VINYL RESINS

Resin Type	Production Period	No. Blends Analyzed	% Blends			Average VCM, ppm
			<100 ppm	100-500 ppm	>1000 ppm	
QSAN-7	June, 1974	96	26	53	9	351
	July, 1974	88	22	59	8	365
QSQH-7	April-May, 1974	51	0	73	4	400
	July, 1974	16	0	88	0	343
QSAH-7	May, 1974	20	0	5	50	1125
	July, 1974	18	6	17	17	724
VSJE-10	May, 1974	8	0	50	13	511
	July, 1974	14	0	93	0	281

UCC
061296

TABLE 11

ANALYSIS OF SUSPENSION VINYL RESIN QSAN-7 FOR RESIDUAL VCM

Blend No.	Date	Container	VCM, ppm	Blend No.	Date	Container	VCM, ppm
B-5404	7-8	900	167	B-5463	7-21	683	135
B-5406	7-9	55252	153	B-5465	7-19	765	431
"	"	"	3	B-5468	"	630	2660
"	"	"	177	B-5470	"	324	197
B-5408	"	"	172	B-5473	7-22	729	1213
B-5410	7-8	655	295	B-5475	7-23	627	122
B-5412	"	857	425	B-5477	7-20	582	154
B-5414	"	826	172	B-5478	"	345	450
B-5416	7-10	496	146	B-5480	7-22	702	95
B-5418	7-11	714	600	B-5482	7-23	501	137
B-5420	7-12	532	1558	B-5484	"	286	213
B-5422	7-16	57100	156	B-5486	7-25	159	269
"	"	"	288	B-5489	7-20	329	1837
"	"	"	485	B-5490	7-21	841	447
"	"	"	527	B-5492	7-22	311	514
B-5424	7-13	566	85	B-5494	7-23	707	57
B-5426	"	757	121	B-5496	7-24	565	323
B-5428	7-19	57101	246	B-5499	7-27	103	321
"	"	"	79	B-5500	7-24	496	84
"	"	"	22	B-5502	"	768	324
"	"	"	37	B-5504	"	842	921
B-5430	7-13	642	292	B-5506	7-26	701	90
B-5432	"	711	244	B-5508	7-25	295	167
B-5434	7-15	567	183	B-5510	"	55257	387
B-5436	7-16	806	29	"	"	"	941
B-5438	7-13	883	176	"	"	"	1593
B-5440	7-15	860	240	"	"	"	237
B-5444	"	672	295	B-5572	"	549	231
B-5446	7-13	825	264	B-5514	"	678	1138
B-5448	7-15	525	157	B-5516	7-26	301	404
B-5450	7-18	57029	89	B-5519	"	597	34
"	"	"	106	B-5521	"	512	268
B-5452	7-17	517	93	B-5522	7-29	57070	81
B-5454	"	649	347	"	"	"	86
B-5456	7-20	55392	109	"	"	"	66
"	"	"	115	"	"	"	56
"	"	"	709	B-5524	7-27	548	77
B-5458	7-18	647	62	B-5526	7-30	609	141
"	"	"	520	B-5528	7-31	595	360

UCC
061297

TABLE II (Continued)

ANALYSIS OF SUSPENSION VINYL RESIN QSAN-7 FOR RESIDUAL VCM

<u>Blend No.</u>	<u>Date</u>	<u>Container</u>	<u>VCM, ppm</u>
B-5529	7-30	147	1375
B-5531	7-27	327	642
B-5533	7-28	702	183
B-5535	7-27	532	642
B-5537	7-29	631	300
B-5539	"	461	153
B-5540	7-30	769	380
B-5542	7-31	780	225
B-5544	"	586	254
B-5546	8-1	672	89

UCC
061298