

23
243
CG 03 CODE KY-787-D PKG. _____
→ JAN 16 33856
EST. WGT. 1090 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76
* TYPED BY	
NE 2/12/77	

MAKING NOTES

REMARKS

Total Wgt. 3490#

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS with	WASH TO	TEST AFTER	LOAD	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
	1-17-80	9:50 A		22	46	AGITATION	2000	2	on 6 cars	STARTED	4:30				
										CAKES USED	7/6				
										WATER ON	8:00 AM				
										HRS. WASHED	2				
										OHMS	3000				
										HRS. WASHED					
										OHMS					
										HRS. WASHED					
										OHMS					
										CAKE CONDITION	6				
										NO. CARS LOADED					
										EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY

RELEASED BY

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 150°F.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYLUMP WGT.
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °FSCREEN
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

DATE MIXED

SAMPLES 1 ENV & 1 Pt. can

DELIVER TO C T L

SAMPLED BY

RELEASED BY

N 2618

14 ds
6 car

2.65
2.76
2.66
2.66
2.69
2.64
2.62
2.64
2.73
2.71
2.76
2.83
2.77
1.61
34.55 T