

CG 03 CODE KY-907-D PKG.

→ JAN-2 33574

EST. WGT. 1080 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-907-D (D)APPROVED BY
EWK 12/12/77

DCG 12/13/77

TYPED BY
rj 2/6/78

MAKING NOTES

REMARKS

TOTAL WGT. 3480#

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240	275				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		1-2-80				STARTED	1AM				
TIME		340P				CAKES USED	46				
RELEASED BY		406				WATER ON	6AM				
PRESS	2	22	23	24		HRS. WASHED	3				
NO. OF CAKES	46	46	46	52		OHMS	3500				
PRESS with						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 2						HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	4				
						EXPLAIN LOSSES					

SAMPLES 8oz Jar
DELIVER TO CIL for Color

SAMPLED BY

RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS
LUMP WGT.
RELEASED BY

-GRINDING-

MILL 939 HSP 1/8"RP SCREEN 3500 RPM
MAX. TEMP. 170°FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

DATE MIXED

SAMPLES 1 ENV & 1 PTCAN

DELIVER TO C T L

SAMPLED BY

RELEASED BY

33574
41
371

11 dm
4 cars