

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

RD-906

LOT

35793

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PO

2468

1

T

#25

2504

1

T

#189

STUMP

4972

TOTAL NET WT.

4972

PKG. N-CODE

PROD. SPVR.

11/3

DATE

5/30/80

WHSE. OPER.

IN34314

24/245
CG 04 CODE KO-906-D PKG.
EST. WGT. 1377 LBS.

MAY 14 1980

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KO-906-D (C)
APPROVED BY
EWK 1/24/78
DCG 1/26/78
TYPED BY
rj 3/6/78

MAKING NOTES

REMARKS

TOTAL WEIGHT 5077# (Req.)

NAME: KROLOR® ORANGE R

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT				245		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE				5-26-80		STARTED	5:15 AM				
TIME				10:30 A		CAKES USED	52				
RELEASED BY				83		WATER ON	8:00 AM				
PRESS	2	22	23	24	25	HRS. WASHED	6				
NO. OF CAKES	46	46	46	52	48	OHMS	11000				
PRESS with						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 3						HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION	6				
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 8.02 Jar
DELIVER TO CTL for color

SAMPLED BY 472 RELEASED BY

-DRYING-

DRY	24 HOURS AT	180 °F	LUMP: - OK - WET - SALTS - CONTAMINATED
Dry on first stage only.			No record of any Processing losses.
Reset every 5 hrs til dry.			ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 18
LUMP WGT. 4957
RELEASED BY

-GRINDING-

MILL 938 HSP 1/8" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 170 °F		MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE / WITHOUT MIXING		DATE MIXED	
SAMPLES 1 Env + 1 Pt can		SAMPLED BY	RELEASED BY
DELIVER TO CTL			

18 dis.

357.93 N
.41 N
.56 N
.00 T

2.91
.12
2.91
.12
3.00
.12
3.01
.12
3.15
.12
3.16
.12
2.94
.12
3.00
.12
2.95
.12
2.77
.12
2.80
.12
2.84
.12
3.01
.12
2.87
.12
2.96
.12
3.23
.12
2.61
.12
1.61
.12
49.57 T