CODE YC-76 LOT E1222

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	58	2700		
	STUMP	LUMP	2735	

TOTAL NET WT. 2900 PKG. N–CODE 1900

PROD. SPVR.	DATE	WHSE. OPER.
	[illegible]	

73
245

CG 01 CODE YC-16-B PKG. 93

→ MAY -0-81-E-1222

EST. WGT. 3130 LBS.

AV2/H

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(A) YC-16-B	A.C 4-7-75
	JFH 5-5-75
	DCG 5-4-75
TYPED BY	

MAKING NOTES

REMARKS

AME: MOLYBDATE ORANGE

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
AT	245				
ATE	5-5				
IME	640				
ELEASED BY	SG				
RESS		91	93	2	25
O. OF CAKES	42	32	32	32	32

RESS AGITATION

ASH TO 2000 OHMS

EST AFTER 2 HOURS WITH 35-75 F WATER

OAD ON 4 CARS

AMPLES

DELIVER TO

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	5AM				
CAKES USED	34				
WATER ON	9PM				
HRS. WASHED	5				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY BLL

-DRYING-

DRY 16 HOURS AT 220 F

LUMP: - OK - WET - SALTS - CONTAMINATED

DRYER SECTIONS USED:

No Record of any Processing Losses
Possible color Left on Ext. Box.

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 10

AMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 2735

SAMPLED BY RELEASED BY [illegible]

-GRINDING-

MICROATOMIZE

SET ROOF GATE AT 5 INCHES AIR FLOW

MAGNEHELIC READING ON ATOMIZER PANEL 1.0"

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 ENV

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096190

1222
124
41

3.01	+
0.14	-
2.89	+
0.14	-
2.92	+
0.14	-
3.09	+
0.14	-
3.06	+
0.14	-
3.13	+
0.14	-
3.32	+
0.14	-
3.07	+
0.14	-
2.87	+
0.14	-
1.39	+
0.14	-
27.35	*

DUP050096191