


FORMULA RECORD

	X	½ Bbl.	Bbl.	2 Bbl.	Code No.	Percent	Manufacturing Specifications
1	Gal.	Neutral Mixing			V-131		Color
2	"	Spar Varnish			V-135-A		Kind of Oil
3	"	F.P. Rosin Ingredient			V-213-A		Per cent
4	Lbs.	Kauri Gum			R-2		Viscosity
5	"	Ester Gum			RE-12		Analysis
6	"	Rosin			R-11		
7	"	Indo Yellow			YN-6		

Formula V-1229
Date 9-15-28 Old No.
Classification

N12385

GLD060166

FORMULA RECORD

A 450 5m 5-25

Goods Papalac Enamel-Golden Brown — Formula V-1229-A

Consistency — Date 7-16-25 Old No.

For Use on — Classification

1/2	6	1/2 Bbl	Bbl.	2 Bbl.	Code No.	Per cent	Manufacturing Specifications
2	Gal.	Neutral Mixing			V-131		Grind
2	"	Spar Varnish			V-135-A		Kind of Mill
4	"	W.P. Dark Japalac-A			V-218-A		Rate per hr.
4	lbs.	Burnt Sienna			S-21		Strainer
3	"	Burnt Umber			BU-17		Analysis
4	"	Pulp			W-11		
16	"	Woods Yellow			YW-6		

GLD060167

FORMULA RECORD

A 430 Im 1-28
Printed in U.S.A.

Goods: Japalac Enamel - Golden Brown Formula No. Y-1229-B

Consistency Date 8-3-28 Old No.

For Use on Cost Classification

1	5	½ Bbl	Bbl.	2 Bbl.	Code No.	Per cent	Manufacturing Specifications
25	gal.	Neutral Mixing			V-131		Grind
25	"	No. 2 Oil			V-202-A		Kind of Mill
43	"	W. P. Dk. Japalac			V-218-A		Rate per hr.
2	"	E-Japan			D-5		Strainer
5	"	Varnolene			S-43		Weight per Gallon
50	lbs.	Burnt Sienna			R-21		Light Baume Temp.
37 1/2	"	Burnt Umber			BR-17		Heavy Baume Temp.
200	"	Woods Yellow			YW-6		Viscosity Temp.
50	"	asbestine Pulp			W-11		Make of Viscosimeter
							Flash Point
							Is Agitator Package Required
							Remarks
Yield							

GLD060168

M-47-6M-11-40 PRINTED IN U.S.A. (B CO.)

COST DEPARTMENT RECORD

Classified Formula No. 4-1229C(N)

Goods JAPALAC ENAMEL-GOLDEN BROWN-(TEMP. RD6) Laboratory Formula No.

Consistency R.M. Date 2-13-41 Factory Letter No. R-071-178

For Use on Production No.

Customer Cost Classification

Ingredient Code Number	Lab'ty Formula	Large Batch Pounds	Large Batch Gallons	Do not write in these columns For Cost Department Use Only	Manufacturing Specifications
W-77	1 7/8	120			Grind "A"
BN-17	7/8	24			Kind of Mill Stone
R-21	3/4	48			Strainer Tinc
YW-2	7/16	28			Weight per Gallon
YW-37	3/32	6			Light Baume Temp.
W-11	1 1/4	80			Heavy Baume Temp.
G) V-109	3 1/2		28		Viscosity 127 1/2" Temp 80°
V-119	1 1/2		12		Viscosimeter #4 Ford
V-706	2		16		Flash Point
RVL-1191	1		8		Is Agitator Required
VM-430	3/32		3/4		
8742	Trace				Formulator J. FRYCE
Yield					

GLD060170

N-47 SM 11-40 PRINTED IN U.S.A. (B CO.)

COST DEPARTMENT RECORD

Classified Formula No. 4-1219 D (RM)

Goods JAPALAC ENAMEL - GOLDEN BROWN

Laboratory Formula No.

Consistency R.M. Date 6-12-41

Factory Letter No. R-061-021

For Use on

Production No.

Customer

Cost Classification

Ingredient Code Number	Lab'ry Formula	Large Batch: Pounds	Large Batch: Gallons	Do not write in these columns For Cost Department Use Only						Manufacturing Specifications
R-21	11½	96								Grind "A"
BN-17	3/4	48								Kind of Mill Stone
4W-2	13/32	70								Strainer Fine
167-9206	½	32								Weight per Gallon
W-91	3/4	48								Light Baume Temp
W-11	¼	16								Heavy Baume Temp
VM-308	1/16	4								Viscosity 1150" Temp 80°
G) V-850	3¾		30							Viscosimeter #4 Ford
V-318	3¾		30							Flash Point
S-43	½		4							Is Agitator Required
D-29	1/8		1							
D-44	1/16		½							Formulator J. FRYCE
Yield										

GLD060171

490-2 SOM 6-40 PRINTED IN U.S.A. (WP)

FORMULA RECORD

Goods Spatter Enamel Golden Brown Formula No. V1249

Consistency Enamel Date 4/24/41 Laboratory No.

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
6397			14	57						Grind R.
8423			2	1						Kind of Mill Stone
V316		2	4	1						Strainer
1011			8	1						Weight per Gallon 9 lbs 2
V308			1	1 cut						Light Baume Temp.
										Heavy Baume Temp.
V273	3¾									Viscosity 110 Temp.
V312	3¾									Viscosimeter
5423	½									Flash Point
										Is Agitator Required
4429			2	2 lbs 4 oz						Remarks Harvard
8423			1	" "						Blue
										1 PW
		Changed to new Master Formula								
					11	4	6			Mix Porcelain
Bond in V850										Panel
Yield										

DISCONTINUED SEE 11-7-41

GLD060172

N-47 SM 11-49 PRINTED IN U.S.A. (B CO.)

COST DEPARTMENT RECORD

Goods: Jafalac Chemical Golden Banana (Rdy) — Classified Formula No. 404

Consistency: — Date: 4/24/52 — Laboratory Formula No. 2 TEMP.

For Use on: — Factory Letter No. P-032-052

Customer: — Production No.

Cost Classification

Ingredient Code Number	Lab'ty Formula	Large Batch Pounds	Large Batch Gallons	Do not write in these columns For Cost Department Use Only	Manufacturing Specifications
YW-2		32			Grind "A"
R-21		48			Kind of Mill STONE
BN-17		16			Strainer
W-77		48			Weight per Gallon 10#
YW-37		8			Light Baume Temp.
W-11		32			Heavy Baume Temp.
W-10		64			Viscosity 140" ± 5" Temp.
2-KB-74			44		Viscosimeter
RVL-123			16		Flash Point
S-13			4		Is Agitator Required
D-40			3/4		
CH-189 SUB.			12 L.D.		Formulator Schaffer
Yield					

GLD060173

4800 25M 1-41 PRINTED IN U.S.A. WPI

FORMULA RECORD

Goods JAP-A-LAC ENAMEL GOLDEN BROWN Formula No. Y 1229 G

Consistency Date 9-26-41 Laboratory No.

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specification
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
R 237			14							Grind A
BN 23			4							Kind of Mill STONE
YW 6		2	4							Strainer
W H			8							Weight per Gallon 9 1/4#
VM 308			1							Light Baume Temp.
										Heavy Baume Temp.
V 706 S	4									Viscosity 110-120" Temp.
V 318 A	4									Viscosimeter
										Flash Point
D 29			2 1/2 OZ TO GAL							Is Agitator Required
D 2A			1 " "							Remarks
GRIND IN V 706 S										MATCH PORCELAIN PANEL
CHANGED BECAUSE V 550 NOT AVAILABLE										
Yield										HAYWARD

DISCONTINUED
SEE NOTE
(11/14/41)

GLD060174

MOLD 28M 1-41 PRINTED IN U.S.A. (WP)

FORMULA RECORD

DISCONTINUED

Goods Japalac Eng. Golden Brown Formula No. Y1229E

Consistency Liquid Date 11-19-41 Laboratory No.

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Parts	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
R237			14					2		Grind a
BR23			4			Acc. page only				Kind of Mill Stone
YW6		2	4						1	Strainer
W11			8							Weight per Gallon 9 7/8
VM308			1							Light Baume Temp.
										Heavy Baume Temp.
V706-8	4									Viscosity 40-120" Temp.
V705-CL	4									Viscosimeter
										Flash Point
D29			2	Lg. to gal						Is Agitator Required
D2A			1	" "						Remarks
										Hayward
										Match Porcelain
				DISCONTINUED						Panel
				SEE Y1229						
				7/12/43						
Yield										

GLD060175

400-O 5014 PRINTED IN U.S.A. (6)

FORMULA RECORD

Goods [illegible] Formula No. [illegible]

Consistency [illegible] Date [illegible] Laboratory No. [illegible]

For Use on [illegible] Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
[illegible]			[illegible]					[illegible]		Grind [illegible]
[illegible]			[illegible]					[illegible]		Kind of Mill [illegible]
[illegible]		[illegible]	[illegible]					[illegible]		Strainer
[illegible]			[illegible]					[illegible]		Weight per Gallon [illegible]
										Light Baume Temp.
[illegible]	[illegible]						[illegible]			Heavy Baume Temp.
[illegible]	[illegible]						[illegible]			Viscosity [illegible] Temp.
[illegible]	[illegible]						[illegible]			Viscosimeter
[illegible]	[illegible]						[illegible]			Flash Point
										Is Agitator Required
[illegible]			[illegible]	[illegible]			[illegible]			Remarks
[illegible]			[illegible]	[illegible]			[illegible]			[illegible]
										[illegible]
	[illegible]									[illegible]
Yield										

DISCONTINUED
SEE # 1229-Y 3/23/45

GLD060176

480-D SDM 2-44 PRINTED IN U.S.A. (B)

FORMULA RECORD

Goods Opaline Yellow Brown Enamel Formula No. 4-1229E

Consistency Date 3-23-45 Laboratory No.

For Use on Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
R 237			14					70		Grind A
BW 23			4					20		Kind of Mill 3 Roll
4W 6		2	4					180		Strainer
OW 181			8					40		Weight per Gallon 9 1/2
W 104			2					10		Light Baume Temp.
										Heavy Baume Temp.
V 357	1 1/2						15-			Viscosity 86-90 Temp.
VR 45016	5 3/4						57 1/2			Viscosimeter
063	1/2						5			Flash Point
543	1/4						2 1/2			Is Agitator Required
										Remarks Hayward
VM 524		1	4 3/4				17 1/2			
D 13		1	2				1 1/4			Match Porcelain panel 1.45 oil/gal.
replaced 1-29										
	Changed to new Opaline Quality									
Yield										J.P.W.

Standard Formula
Not to be taken
from File.

GLD060177

Characteristics and Method of Using	Cost Data				Customers
Type of Goods					
Color					
Luster					
Match for					
Kind of Reducer					
Amount of Reduction for					
Brushing					
Spraying Pressure					Aeroplanes 3-29-45
Dipping Drip Time	Analysis				
Flocoing Drip Time	Pigments				34.5% Toronto 8/27/4
Tumbling	Titanated Pigment			21.9%	
Air dry to recoat	Iron Oxide Red			6.2%	
To Sand or Rub	Phthalic Alkyd			56.4%	
Bake Time Temp.	Mineral Spirits			12.1%	
Rub with	Lead Co Naphthenate			3.4%	
Polish with				100.0%	
Schedule	Vehicle			65.5%	
	Phthalic Alkyd			26.9%	
	Petroleum Oil			4.6%	
	Mineral Spirits			2.7%	
	Liquid Driers			2.8%	
				100.0%	

GLD060178