

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE RT428 LOT 37684

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

18 3039 33TOTAL NET WT. 3039 PKG. N-CODE

PROD. SPV. DATE WHSE. OPER.

245 11/71 292

N35087

O.T

182.+
177.+
181.+
188.+
173.+
162.+
166.+
155.+
182.+
156.+
171.+
190.+
198.+
193.+
176.+
163.+
66.+
160.+
3039.T

96
903
CG 32 CODE RT-428-D PKG.
→ OCT 31 80 37684
EST. WGT. 3068 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
RT-428-D (V) APPROVED BY
JUG 12-10-76
DCG 08-10-78

TYPED BY
emw081878

MAKING NOTES

REMARKS

NAME: WATCHUNG® RED B

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT	903				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-31				STARTED	1254				
TIME	10:45				CAKES USED	35				
RELEASED BY	237				WATER ON	6A				
PRESS	95	96			HRS. WASHED	11				
NO. OF CAKES	76	88			OHMS	5000				
PRESS	with	AGITATION			HRS. WASHED					
WASH TO	3000	OHMS with 35-75°F water			OHMS					
TEST AFTER	3	HOURS			HRS. WASHED					
LOAD	on 10 cars				OHMS					
1.	Press Immediately Code				CAKE CONDITION					
2.	Instruct Making Area to add 10# N-588-A halfway thru pressing				NO. CARS LOADED	67-5				
3.	Clean magnetic separator after pressing				EXPLAIN LOSSES					
	Cleaned by	Time cleaned.								

SAMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

- DRYING -

DRY 20 HOURS AT 220 °F LUMP: - OK - WET - SALTS - CONTAMINATE
Hold on track 30 min before dumping

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

NO. DRUMS 15

LUMP WGT. 3050

RELEASED BY

- GRINDING -

MILL 2 HSP 1/8" RP SCREEN 3350 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 2 ENV

DELIVER TO CTL

DATE MIXED 11/4/80

SAMPLED BY 213

RELEASED BY

37604

51

58

213

14

207

14

225

14

215

14

224

14

222

14

225

14

224

14

219

14

200

14

151

14

37634

5100

18

0

2174

230

12

218

12

242

12

234

12

3050