

COST DEPARTMENT RECORD

Goods: *Endurance Shade White Base* Formula No. *V18040 Ten*
 Consistency: _____ Date: *5/16/49* Laboratory No. _____
 For Use on: _____ Cost Classification _____

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Oz.	Pints	Lbs.	Oz.	Pints	Lbs.	Oz.	
<i>W69</i>		<i>2</i>	<i>13</i>							Grind <i>1-2</i>
<i>W35</i>		<i>5</i>	<i>15</i>							Kind of Mill <i>Pebble</i>
<i>W104</i>		<i>1</i>	<i>14</i>							Strainer
<i>W11</i>		<i>3</i>	<i>71</i>							Weight per Gallon <i>15.5</i>
<i>01</i>	<i>2 1/16</i>									Light Baume Temp.
<i>05</i>	<i>1 7/16</i>									Heavy Baume Temp.
<i>0286</i>	<i>1 7/8</i>									Viscosity <i>85-90</i> <i>K</i>
<i>D15</i>	<i>5/8</i>									Viscosimeter <i>Krebs</i>
<i>S43</i>	<i>1 3/4</i>									Flash Point
<i>add Per</i>										Is Agitator Required
<i>FEQ 0183</i>										Remarks <i>A.S. 72 hrs</i>
<i>shlps</i>										
<i>M25</i>		<i>as needed</i>								
<i>6000</i>	<i>0.0-0.1</i>	<i>43.33%</i>								<i>J. Wanganer</i>
<i>6000</i>	<i>0.0-0.5</i>	<i>23.33%</i>								<i>Lab</i>
<i>Yield</i>	<i>0.026</i>	<i>33.33%</i>								

N12035

GLD058984

