

<u>Code</u>	<u>Description</u>	<u>Pigment</u> <u>Volume</u> %	<u>Non-Volatile</u> <u>Volume</u> %	<u>Gloss</u>	<u>Fl</u>
301-756	Prewar #40 Outside White (obsolete)	28	92.0	High	N
301-756	Oil Saving #40 Outside White (obsolete)	35	72.8	medium-	b
301-827	Oil saving Outside White: all linseed	"	73.6	medium	c
301-836	Oil saving Outside White: 20% soya on oil	"	"	medium-	c
301-838	Oil saving Outside White: 57% #500 selected soya oil	"	"	medium	c
301-829	Lead-free oil saving Outside White: all linseed	"	73.5	low	b
301-850	Lead-free oil saving Outside White: 57% #500 selected soya oil	"	"	low	b
301-839	"Trenton" White: 70% soya, 5% glyceryl phthalate	"	"	low	c
P-301-P-28248	1945 House tests: all linseed, lead- free	"	83.0	low	c
P-301-P-28247	" " " " " "	40	76.2	v. low	b
P-301-P-58578	1946 House tests: all linseed, lead- zinc	35	82.4	low	v
P-301-P-58591	" " " " " "	40	"	v. low	b
P-301-P-86265	1947 House tests: all linseed, lead- free	35	"	low	s
P-301-P-77873	1947 House tests: all #500 selected soya oil, lead-free.	"	"	low	b

N50721

DUP150049412