

- 61 -

FORMULAE OF SPECIFIED PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MANUFACTURER 'C'

Outside White House Paint

Percentage Formula		Percentage Formula	
December 1940 to October 1941		November 1941 to June 1942	
	Percent		Percent
<u>Pigment</u>	71.6	<u>Pigment</u>	71.2
Lithopone	31.2	H. O. Lithopone	31.1
35% Leaded Zinc	29	35% Leaded Zinc	28.9
White Lead	26.8	White Lead	23.5
Magnesium Silicate	11.6	Magnesium Silicate	15.1
Titanium Dioxide	1.4	Titanium Dioxide	1.4
	100.0		100.0
<u>Vehicle</u>	28.4	<u>Vehicle</u>	28.2
Alkali Refined Linseed Oil	82	Alkali Refined Linseed Oil	77
Thinners and Driers	18	W.H.B. Oil	6.93
	100	Thinners & Driers	16.07
	100.0		100.00
			100.0

Inside Flat White Paint

Percentage Formula

November 1940 to June 1942

	Percent
<u>Pigment</u>	59.3
Titanium Calcium Pigment	90.50
Silica	9.05
Suspending Agent	.45
	100.00
<u>Vehicle</u>	40.7
Varnish and Oil	57
Thinners and Driers	43
	100
	100.0