MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky·787 LOT 34611

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1520	1	T. 102		
1490	1	T. 330		
	STUMP			

TOTAL NET WT. 3010 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	3, 6 80	

N 26293

DUP050093721

22/243

CG 03 CODE KY-787-D PKG. ____

→ FEB28 34611

EST. WGT. ~~1090~~ 990 LBS. OK/FP

TOTES

Total Wgt. ~~3490#~~ 3390

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-787-D (R)	EWK 9/22/76
	Alternate	DCS 9/22/76
	TYPED BY	
	NE 2/12/77	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM NON-BLEEDING

INSTRUCTIONS **-PRESSING-** **RECORD**

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	243					STARTED	7PM				
DATE	3-2-80					CAKES USED	46				
TIME	6:50 PM					WATER ON	10 Bar				
RELEASED BY	C.M.					HRS. WASHED	8				
PRESS	22	23	~~23~~	24		OHMS	600				
NO. OF CAKES	~~46~~	46	~~46~~	52		HRS. WASHED					
PRESS with		AGITATION				OHMS					
WASH TO 2000		OHMS with 35-75°F water				HRS. WASHED					
TEST AFTER 2		HOURS				OHMS					
LOAD on 6 cars						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

No Record of any Processing Losses

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 13

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 3099
SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN R.P.M
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 Pr. can
DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

N 26293.01

DUP050093722

34611
41
354
6

0.00	*
2.55	+
0.14	-
2.53	+
0.14	-
2.54	+
0.14	-
2.69	+
0.14	-
2.57	+
0.14	-
2.61	+
0.14	-
2.52	+
0.14	-
2.67	+
0.14	-
2.61	+
0.14	-
2.50	+
0.14	-
2.65	+
0.14	-
2.87	+
0.14	-
1.50	+
0.14	-
30.99	*

DUP050093723