

... J. J. McCarthy
E. Bonet
R. K. Hoagland
H. Forlisi
E. C. Lindstrom, DEQ
H. Bauman
File (2)
E/T (1)

JOHNS-MANVILLE
CONTROL LABORATORY
MANVILLE GENERAL PLANT

Report: CS-15414
Date: 5-27-57



Subject: Blended Blue Crocidolite Asbestos Fibre - 20 Tons
Requested by: R. K. Hoagland
Identification: Rec'd 5/6/57 from the Asbestos Corporation of America
Order #M-6177 - Requisition C-141

SUMMARY:-

The 20 tons of Blended Blue Crocidolite Asbestos Fibre received 5/6/57 pass
P.S. II-1983.

DATA:-

McNett Test Method TX 10.15 - Percent

Sample	1	2	Average	P.S. II-1983-1	
				Min.	Max.
+14 Mesh Fibre & Rock	39.8	38.8	39.3		
+14 Mesh - Rock	----	----	----	0	2
+14 Mesh - Fibre	39.8	38.8	39.3	30	50
+28 Mesh	5.5	5.6	5.6	0	13
+100 Mesh	8.6	7.7	8.1	0	16
Cum. +100 Mesh	53.9	52.1	53.0	--	--
+200 Mesh	6.1	5.6	5.9	0	16
-200 Mesh	40.0	42.3	41.1	36	56

cjp

APPROVED: R. Jacobs

REPORT BY: W. J. Hesterhagen

002270

