CG 01 CODE YE-698-D PKG ____

LOT L2H02

EST. WT. 5527* LBS.

YE-698-D (T) FWP 10/18/82
ALTERNATE

COMTYP JOB NAME: 01YE698DPT

MAKING NOTES: _____

= PRESSING =

INSTRUCTIONS					RECORD					
VAT	247				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-28				STARTED					
TIME	5:00PM				CAKES USED					
RELEASED BY	[illegible]				WATER ON					
PRESS	2	92	93		HRS. WASHED					
NO.OF CAKES	54	54	54		M MHOS					
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER					M MHOS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD ON 7 CARS					M MHOS					
					CAKE CONDITION					
					NO CARS LOADED					
					EXPLAIN LOSSES					
SAMPLES 8 OZ					SAMPLED BY					
DELIVER TO CTL.					RELEASED BY					

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F

(NOT EXTRUDED) DRY 10 HRS AT 240 F

SAMPLE

DELIVER

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO CARS PULLED NO DRUMS
LUMP WGT

SAMPLED BY

RELEASED BY

CO-GRIND PER CTL INSTRUCTIONS GRINDING

MILL MIKROATOMIZE SCREEN RPM

MAX. TEMP DEG F

SET ROOF BLAST - GATE AT "5." FOR HIGH AIR FLOW

SAMPLE W/O MIXING

SAMPLES 1 ENV & 1 PINT CAN IF GROUND SEPARATELY

DELIVER TO CTL

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY

RELEASED BY