CODE 11C-16B LOT 21353

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	62	3100		
	STUMP	Lum P3121		

TOTAL NET WT. 3100 PKG. N–CODE 1000

PROD. SPVR. DS DATE 5/15/21 WHSE. OPER.

93
242

CG 01 CODE YC-16-B PKG. 93

→ MAY -0-81-E-1338

EST. WGT. 3130 LBS.

Red
HP

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	(A) YC-16-B	AJC 4-7-75
		JFH 5-5-75
		DCG 5-14-75
	TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE

NON-BLEEDING

EE INSTRUCTIONS — -PRESSING- — RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	242					STARTED	8AM				
DATE	5-12					CAKES USED	34				
TIME	6 AM to 4PM					WATER ON	2PM				
RELEASED BY	233					HRS. WASHED	3				
PRESS	91	92	93	2	25	OHMS	2500				
NO. OF CAKES	42	32	32	32	32	HRS. WASHED					
PRESS		AGITATION				OHMS					
WASH TO	2000	OHMS				HRS. WASHED					
TEST AFTER	2	HOURS WITH 35-75 F WATER				OHMS					
LOAD ON 4 CARS						CAKE CONDITION					
						NO. CARS LOADED	4				
						EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY — RELEASED BY

-DRYING-

DRY 16 HOURS AT 220 F

LUMP: - OK - WET - SALTS - CONTAMINATED

DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES
DELIVER TO

NO. CARS PULLED 4 — SAMPLED BY — LUMP WGT. 3121 — RELEASED BY

-GRINDING-

MICROATOMIZE
SET ROOF GATE AT 5 INCHES AIR FLOW
MAGNEHELIC READING ON ATOMIZER PANEL 1.0"

SCREEN — RPM
MAX. TEMP. — °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO C T L

DATE MIXED

SAMPLED BY — RELEASED BY

DUP050096147

16
1338
41
56

0.00 *

2.83 +
0.12 -
2.97 +
0.12 -
2.83 +
0.12 -
2.82 +
0.12 -
2.73 +
0.12 -
2.86 +
0.12 -
2.82 +
0.12 -
2.74 +
0.12 -
3.02 +
0.12 -
2.70 +
0.12 -
2.23 +
0.12 -
29.23 *

0.00 *

29.23 +
2.10 +
0.12 -
31.21 *

DUP050096148