

PACKAGE TYPE		DATE AND PART NUMBER	
CODE	NO. PAGES	DATE	PART NUMBER
50	122	6/100	
TOTAL NET WT		PKG. N-CODE	
6/100		1000	
PROD. SVR.	DATE	WHS. OFF.	
TV	10/20/80		

N34960

CG 03 CODE KY-907-D PKG.

OCT-23 80 37584

EST WGT. 1853 LBS

PROCESSING INSTRUCTIONS: BATCH UNM

PROCESSES

KY-907-D (E)

Alternate

APPROVED &

FWK 12/12/

DCG 12/14/

TYPED BY

ci 2/8/77

MAKING NOTES

REMARKS

TOTAL WGT. 6053#

NAME: KRULORTM YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

AT	246			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	10-24-80			STARTED	3:00				
IME	130A			CAKES USED	68				
RELEASED BY	95			WATER ON	7:30A				
RESS	96			HRS. WASHED	7				
OF CAKES	72			OHMS	2500				
RESS With				HRS. WASHED					
ASH TO 2000				OHMS					
ST AFTER 3				HRS. WASHED					
AD on 10 cars				OHMS					
				CAKE CONDITION					
				NO CARS LOADED					
				EXPLAIN LOSSES					

AMPLES 802 Jar
FLIVER TO CTL for color

SAMPLED BY

RELEASED BY

-DRYING-

24 HOURS AT 180 °F

LUMP: - OK - WET - SALTS - CONTAMINAT

ADDITIONAL DRYING HOURS REQUIRED

NO CARS PULLED
SAMPLED BY

NO. DRUMS

LUMP WGT. 6016

RELEASED BY B66

-GRINDING-

11 1150 HSP 1/8" RP SCREEN 3500 RPM
- X 11MP 170°F

SCREEN	RPM
MAX. TEMP.	° F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY

RELEASED BY

37584
41
231

37584
41
100

0.00 *
0.0-M+

3.25 +
0.12 -
3.15 +
0.12 -
3.25 +
0.12 -
3.25 +
0.12 -
3.15 +
0.12 -
3.10 +
0.12 -
3.05 +
0.12 -
3.10 +
0.12 -
3.05 +
0.12 -
1.60 +
0.12 -
28.75 *
28.75M+

28.75 +
3.08 +
0.12 -
3.31 +
0.12 -
3.08 +
0.12 -
2.89 +
0.12 -
3.10 +
0.12 -
2.96 +
0.12 -
3.01 +
0.12 -
3.19 +
0.12 -
3.00 +
0.12 -
3.00 +
0.12 -
2.11 +
0.12 -
60.16 *
60.16M+