

VISCOSITY WORK SHEET

Item 2109 P.T.No. _____ Date 9-27-54
 Worker BPS Polymer Lucite Solvent EDC
 For Bl Martin's Charge 1242 Temperature 25°C
 Viscometer No. _____ Efflux Time 235.3 / 235.8 Weight: Gross 5.6129
 Viscometer No. _____ Efflux Time 220.0 / 119.2 Tare 5.4879
 Viscometer No. _____ Efflux Time _____ Net 1.1250

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Inh. visc. Visc. or M.W.
5711	502	1	289.9, 289.9	1.232 96,500 ✓
	140	2	270.5, 270.5	1.230 96,000
5713	21	1	288.2, 288.2	1.227 94,000 ✓
	e	2	270.7, 270.7	1.229 95,000
5715	M33	1	288.9, 288.9	1.230 96,000 ✓
	506	2	269.6, 269.6	1.228 95,000
5716	K9	1	291.1, 291.2, 291.1	1.232 96,500 ✓
	e	2	268.5, 268.2, 268.2	1.230 96,000
5717	17	1	290.1, 290.1	1.232 96,500 ✓
	18	2	268.7, 269.0	1.230 96,000
recheck 5712	L	1	290.2, 290.2	1.232 96,500