

APR 1 1971

# AROCLOR® 1221, 1232, 1242

*for polyvinyl acetate-emulsion adhesives*

---

TECHNICAL BULLETIN No. PL-321

REVISED  
APRIL, 1963



ST. LOUIS 66, MISSOURI

0509321

TOWOLDMON0034616  
WATER\_PCB-00019085

## INTRODUCTION

Monsanto *Aroclor*\* chlorinated polyphenyls are a series of compounds serving a variety of needs. Each *Aroclor* can serve as a plasticizer for many of the synthetic resins. Properties imparted vary with the *Aroclor* chosen. In this respect the family of *Aroclor* compounds is analogous to a series of phthalate esters.

*Aroclor* 1221, 1232 and 1242 are three compounds especially suited for plasticizing polyvinyl acetate (PVA) emulsion adhesives.

These are important advantages of the *Aroclor* plasticizers specified —

- 1) Excellent tack and strong bonding power are imparted to PVA adhesives.
- 2) The compounds are low in cost.
- 3) The plasticizers are light colored.
- 4) *Aroclor* 1221, 1232 and 1242 are mobile liquids at room temperature. Plant handling is simplified since no pre-melting is required.
- 5) The plasticizers are readily blended with PVA emulsions by simple stirring.
- 6) The hardness desired in various adhesive applications can be varied by choice of *Aroclor* plasticizer without materially changing other properties of the adhesive.
- 7) The three *Aroclor* plasticizers recommended for PVA emulsion adhesives are comparable to *ortho*-Nitrophenyl, which has been displaced by these *Aroclor* plasticizers in PVA emulsions, with regard to tack and fiber-tear, as indicated by tests on a porous yellow paper and a melamine-coated Kraft stock.
- 8) *Aroclor* compounds are readily available.

\**Aroclor*: Monsanto Chemical Company Trademark. Registered in U. S. Patent Office.

## COMPATIBILITY

Tests conducted by Monsanto show *Aroclor* 1221, 1232 and 1242 are each compatible with PVA at the evaluation level of 11 parts of plasticizer in 100 parts of polyvinyl acetate emulsion.

## LABORATORY DATA

Several PVA adhesive formulations using different plasticizers were made up and evaluated in our laboratories. The basic formulation consisted of 11 parts of plasticizer in 100 parts of polyvinyl acetate emulsion. Data tabulated below will allow the adhesive formulator to choose the most suitable plasticizer for the adhesive properties desired.

### COMPARISON OF POLYVINYL ACETATE PLASTICIZERS (100 parts polyvinyl acetate emulsion; 11 parts plasticizer)

| Formulation Properties                                                      | ortho-Nitro-biphenyl | Dibutyl Phthalate | Aroclor 1221 | Aroclor 1232 | Aroclor 1242 |
|-----------------------------------------------------------------------------|----------------------|-------------------|--------------|--------------|--------------|
| Shore Hardness, A-scale                                                     | 82                   | 69                | 66           | 86           | 97           |
| Low Temp. Flex., ° C                                                        | +2.2                 | -10.2             | -5.9         | +4.0         | +5.3         |
| Volatility (% plasticizer lost after 24 hrs. at 86° C)                      | 3.8                  | 4.0               | 4.8          | 4.3          | 4.0          |
| Kerosene Extraction, (% plasticizer lost after 24 hrs. at room temperature) | 3.2                  | 4.1               | 4.5          | 3.8          | 4.2          |
| Viscosity of Formulation*<br>(Centipoises)                                  |                      |                   |              |              |              |
| Initial                                                                     | 2160                 | 2420              | 2240         | 2160         | .....        |
| 1 day                                                                       | .....                | 2460              | .....        | .....        | .....        |
| 3 days                                                                      | 2200                 | .....             | 2200         | 2060         | .....        |
| 4 days                                                                      | .....                | 2520              | .....        | .....        | .....        |
| 5 days                                                                      | 2280                 | .....             | 2200         | 2040         | .....        |
| 7 days                                                                      | 2340                 | .....             | 2180         | 2020         | .....        |
| 10 days                                                                     | 2460                 | .....             | 2260         | 2060         | .....        |

\*Initial viscosity of the polyvinyl acetate emulsion tested was 1500 centipoises.

# TYPICAL PROPERTIES AND SPECIFICATIONS

| Property                                   | Aroclor<br>1221                    | Aroclor<br>1232                         | Aroclor<br>1242                         |
|--------------------------------------------|------------------------------------|-----------------------------------------|-----------------------------------------|
| Appearance                                 | Mobile, Colorless,<br>clear liquid | Practically<br>colorless,<br>mobile oil | Practically<br>colorless,<br>mobile oil |
| Refractive Index<br>@ 20° C                | 1.617 - 1.618                      | 1.620-1.622                             | 1.627-1.629                             |
| Chlorine, %                                | 21.0±0.5                           | 32.0±0.5                                | —                                       |
| Density, lbs. per gal.,<br>@ 25° C         | 9.85                               | 10.55                                   | 11.50                                   |
| Boiling Point,<br>760 mm Hg                | 275°-320° C                        | 290°-325° C                             | 325°-366° C                             |
| Pour Point<br>(ASTM D-97)                  | Crystals at 1° C.                  | -35.5° C                                | -19° C                                  |
| Flash Point (C.O.C.)                       | 286°-302° F.<br>141°-150° C.       | 305°-310° F.<br>149°-152° C.            | 348°-356° F.<br>176°-180° C.            |
| Fire Point (C.O.C.)                        | 349° F.<br>176° C.                 | 460° F.<br>238° C.                      | None, to<br>boiling point               |
| Viscosity, S.U.S.,<br>@ 37.8° C            | 38-41                              | 44-51                                   | 80-93                                   |
| 54.4° C                                    | 35-37                              | 39-41                                   | 49-56                                   |
| 98.9° C                                    | 30-31                              | 31-32                                   | 34-35                                   |
| Distillation Range<br>ASTM-D-20 (modified) | 275°-320° C                        | 295°-355° C                             | 325°-360° C                             |

## MONSANTO SPECIFICATIONS

| Property                                 | Aroclor<br>1221 | Aroclor<br>1232 | Aroclor<br>1242 |
|------------------------------------------|-----------------|-----------------|-----------------|
| Color, APHA max.                         | 100             | 100             | 100             |
| Specific Gravity<br>A 25/155° C          | 1.182-1.192     | 1.270-1.280     | 1.381-1.392     |
| Acidity, mg. KOH/gm. max.                | 0.014           | 0.014           | 0.015           |
| Viscosity @ 100° F.,<br>S.U.S. (37.8° C) | 38-41           | 44-51           | 80-93           |

## ODOR MASKING FOR SPECIAL APPLICATIONS

When necessary, the slight odor imparted to PVA adhesives by these *Aroclor* plasticizers can be completely and economically masked. One drum of adhesive is effectively masked by the addition of only 6 grams of either Odormasque\* 1004 (camphor odor) or Odormasque 1066 (fruity odor). Thus one pound of Odormasque is enough to treat 75 drums of adhesive. Even after 40 hours' aging at 150° F, the maskant odor was retained by dried adhesive films containing 0.005 per cent Odormasque (based on resin).

\*Odormasque: Registered Trademark of Polak & Schwarz, Inc., New York, N. Y.

## TOXICITY AND SAFE HANDLING

The oral LD<sub>50</sub> of Aroclors 1221, 1232, and 1242 in rats is approximately 4.0 grams, 4.5 grams, and 8.5 grams per kilogram respectively. This indicates that the compounds are not particularly toxic following single oral ingestion.

When the Aroclor compound is applied undiluted to the skin of rabbits the minimum lethal dose is 2 to 3.1 grams per kilogram for "1221", 1.25 to 2.0 grams per kilogram for "1232", and 0.8 to 1.25 grams per kilogram for "1242". In this range of skin absorption doses, the compounds can be classified as "slightly toxic", "mildly toxic", and "moderately toxic" respectively. It is recommended that repeated or prolonged skin contact be avoided.

In animal inhalation studies, Aroclor vapors do not present a hazard if the compounds are used at ambient air temperatures. When used at elevated temperatures, the inhalation of vapors should be avoided.

## SHIPPING

### Shipping Classification

— Chlorinated Diphenyl/Synthetic resin,  
Liquid N.O.I.B.N.

### Shipping Regulations

— None

### Standard Containers

— Aroclor 1221 Tank car, 520 lb. steel drum  
Aroclor 1232 Tank car, 550 lb. steel drum  
Aroclor 1242 Tank car, 600 lb. steel drum

The information contained in this bulletin is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. Monsanto Chemical Company disclaims any liability incurred in connection with the use of these data or suggestions.

Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.



ATLANTA  
BOSTON  
CHICAGO  
CINCINNATI  
CLEVELAND  
DETROIT  
HOUSTON  
LOS ANGELES  
MINNEAPOLIS  
NEW YORK  
PITTSBURGH  
ST. LOUIS  
SANTA CLARA  
SEATTLE  
SYRACUSE  
WILMINGTON  
MONSANTO CHEMICALS LTD.  
London  
MONSANTO CHEMICALS  
(AUSTRALIA) LTD. Melbourne  
MONSANTO (CANADA) LTD.  
Montreal • Toronto • Vancouver

ST. LOUIS 66, MISSOURI

0509326

TOWOLDMON0034621

WATER\_PCB-00019090