

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

LOT

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

STUMP

TOTAL NET WT.

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

PRODUCT NAME: MOLYBDATE ORANGE

CG 01 CODE YE-735-D PKG

LOT *K2J15*
EST. WT. 3839* LBS.

NON-BLEEDING

PROCESSES

YE-735-D (M)

ALTERNATE

APPROVED BY:

FWP 09/22/82

COMTYP JOB NAME: 01YE735DPH

MAKING NOTES:

INSTRUCTIONS

EC
VAT *12424*
DATE *10-5-82*
TIME *12:00*
RELEASED BY *[Signature]*
PRESS 2 91
NO. OF CAKES 32 42
PRESS WITH AGITATION SEE BELOW
WASH TO 285 M MHOS WITH 35-75°F
WATER.
TEST AFTER 2 HOURS.
LOAD ON 5 CARS.
STOP AGITATOR AT ABOUT 50°
DO NOT EXTRUDE.

= PRESSING =

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
M MHOS
HRS. WASHED
M MHOS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

RECORD

1ST	2ND	3RD	4TH	5TH
<i>430</i>				
<i>42</i>				
<i>37</i>				
<i>191</i>				

SAMPLES JAR
DELIVER TO

[Signature]
SAMPLED BY
RELEASED BY *AK*

= DRYING =

DRY 14 HRS AT 240°F MAY 1 - AUG. 31.
DRY 12 HRS AT 240°F SEPT. 1 - APR 30

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

12
4084
200

= GRINDING =

MIKROATOMIZE
SET LUMP FEED SCREW AT 1/2 SPEED
SET BLAST GATE AT 2

MAGNEHELIC READING ON ATOMIZER PANEL
BOARD (1.0°)

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 4 ENV & 2 FT. CANS
DELIVER TO CTE

DATE MIXED

SAMPLED BY
RELEASED BY

15
41
16

0.00 *
3.81 +
0.12 -/
3.85 +
0.12 -/
3.58 +
0.12 -/
3.81 +
0.12 -/
3.64 +
0.12 -/
4.00 +
0.12 -/
3.79 +
0.12 -/
3.87 +
0.12 -/
3.81 +
0.12 -/
3.66 +
0.12 -/
3.43 +
0.12 -/
1.03 +
0.12 -/
40.84 *