

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

4/22/82

CG 01 CODE YE-698-D PKG

PROCESSES APPROVED BY
YE-698-D (S) F. POST 10/09/81
ALTERNATE
TYPED BY JMH

LOT F2J69

JUN 7 1982

EST. WT. 5547* LBS.

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS			= PRESSING =	RECORD					
VAT	242			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	16-10-82			STARTED	10:00 PM				
TIME	11:40 AM			CAKES USED	33				
RELEASED BY	PCY			WATER ON	12:30 PM				
PRESS	2	92	93	HRS. WASHED	6				
NO. OF CAKES	54	54	54	M MHOS	176				
PRESS WITH AGITATION				HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER				M MHOS					
TEST AFTER 2 HOURS				HRS. WASHED					
LOAD ON 7 CARS				M MHOS					
				CAKE CONDITION	5+2				
				NO CARS LOADED					
				EXPLAIN LOSSES					

SAMPLES 8 OZ
DELIVER TO CTL.SAMPLED BY
RELEASED BY S.W FOR ALL

= DRYING =	
(EXTRUDED) DRY 10 HRS AT 240 DEG F	LUMP: - OK - WET - SALTS - CONTAMINATD
(NOT EXTRUDED) DRY 10 HRS AT 240 F	

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

NO CARS PULLED

NO DRUMS 17
LUMP WGT 5596

DELIVER

SAMPLED BY
RELEASED BY

CO-GRIND PER CTL INSTRUCTIONS GRINDING

MILL MIKROATOMIZE SCREEN

RPM

SCREEN

RPM

MAX. TEMP DEG F

MAX. TEMP.

F

SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE

DATE MIXED

SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTLSAMPLED BY
RELEASED BY

N39422

YE698
172069

0.00 *

3 *Drums*

3.64 ✓
0.12 -
3.74 ✓
0.14 -
3.31 ✓
0.12 -
3.53 ✓
0.12 -
3.32 ✓
0.12 -
3.57 ✓
0.12 -
3.53 ✓
0.12 -
3.41 ✓
0.12 -
3.55 ✓
0.12 -
3.72 ✓
0.12 -
3.93 ✓
0.12 -
3.67 ✓
0.12 -
3.15 ✓
0.12 -
2.12 ✓
0.12 -
46.11 *

(17)

3.31 ✓
9.12 -
3.32 ✓
9.12 -
2.25 ✓
0.12 -
9.12 -
9.21 *

4611
925
5536