

Mr. J. E. Southwick

Jan. 31, 1972

Mr. S. T. Howell

Strongsville, DPJNC

cc: Mr. R. J. Haviland-#1
Mr. M. W. Malaga - #1
Mr. J. G. Kingston
Mr. W. M. Tomc

ALKYD GLOSS FUNGICIDAL ENAMEL - Y-5069-F

We are issuing Y-5069-F to reduce the lead content in the dried film to below .5%. This is being accomplished by changing the driers to cobalt zirconium rather than lead cobalt. This change is the same as we made in Spred Gloss Y-900 and the cost increase is 3¢ per gallon. There are no other changes in the physical properties of the paint.

J. E. Southwick

JES/ab

GLD012123