PRATT&LAMBERT

NOXIDE

EQUIPMENT ENAMEL

161 WHITE

Rust-Inhibitive

ONE GALLON

October 1971

0007-PTL-001526

CAUTION! COMBUSTIBLE!

CONTAINS LEAD. HARMFUL IF EATEN. Keep away from heat and open flame. Do not apply on any interior surface of a dwelling, or a place used for the care of children, or on window sills, toys, cribs, and other furniture which might be chewed by children. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use.

Use with adequate ventilation.

KEEP OUT OF THE REACH OF CHILDREN. B44

DIRECTIONS FOR USING NOXIDE EQUIPMENT ENAMEL

A durable rust-inhibitive enamel for interior and exterior work, such as pipe lines, machinery, tractors, farm and other heavy duty equipment. May be used to prime small areas and to spot prime repaint work.

General Information

Never paint a damp, dirty, or greasy surface. Avoid outdoor painting when the weather is cold, frosty, or rainy. Avoid painting surfaces while they are exposed to hot sun.

Thoroughly stir Noxide Equipment Enamel. Use a clean brush and apply paint evenly. If thinning is necessary, add Duosol or mineral spirits. For spraying, thin each gallon with one pint of Duosol or mineral spirits. Clean brushes and equipment in Duosol.

Be sure each coat of paint is dry before applying the next coat.

NEW STRUCTURAL STEEL — Remove mill scale by sandblasting or flame cleaning.

NEW SHEET STEEL — Remove grease and oil with Duosol or mineral spirits. Wire brush or sand rust spots to bright metal.

NEW GALVANIZED STEEL — Remove oil with Duosol or mineral spirits. Before painting, treat with proprietary crystalline zinc phosphate or acid-bound resinous solutions in accordance with manufacturer's directions. Otherwise, allow to weather for at least three months and wire brush.

OLD PAINTED SURFACES — Remove scale, rust, and loose paint with a wire brush or coarse sandpaper. Clean rust spots to bright metal.

Specifications

NEW EXTERIOR WORK — *First Coat:* Noxide One Day Primer or P&L No. 25 Zinc Chromate Primer. *Second and Third Coats:* Noxide Equipment Enamel.

NEW INTERIOR WORK — Two coats Noxide Equipment Enamel.

OLD WORK — Touch up bare spots with Noxide Equipment Enamel, then apply one or two coats over entire area.

RNAG

PRATT&LAMBERT, INC

BUFFALO, NEW YORK 14240

Pratt & Lambert Press—USA