MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky 788 LOT 34978

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	64	3,350		
	STUMP			

TOTAL NET WT. 3,350 PKG. N-CODE 1130

PROD. SPVR.	DATE	WHSE. OPER.
RH	3/24/85	

N 27523

CG 03 CODE KY-788-D PKG. ____

→ MAR 17 34978

EST. WGT. ~~960~~ 860 LBS.

OK
AP

3460

Total Wgt. ~~3560~~# Req(_____)

PROCESSING INSTRUCTIONS: BATCH UNIT

23/240

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/27/76
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

VAT	240				
DATE	3/21/80				
TIME	530				
RELEASED BY	SH				
PRESS	08	23	24		
NO. OF CAKES	46	46	46		

PRESS With AGITATION
WASH TO 2000 OHMS with 35-75°F water
TEST AFTER 2 HOURS
LOAD on 6 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	53 PM				
CAKES USED	54				
WATER ON	6A	~~7:30~~			
HRS. WASHED	6	2 HRS			
OHMS	2000	2000			
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	11	5			
EXPLAIN LOSSES					

SAMPLES 1- 8oz JAR
DELIVER TO CTL for Color

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

Dry 12 hrs at 220 °F HRS.
Then Dry 8 hrs at 160 °F °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums (14)

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 3360
SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO CTL

DATE MIXED
SAMPLED BY RELEASED BY

DUP050094646

N 27523.01

349.78	#
.41	#
3.24	#
.00	T
2.63	
.14	-
2.55	
.14	-
2.53	
.14	-
2.44	
.14	-
2.58	
.14	-
2.53	
.14	-
2.42	
.14	-
2.52	
.14	-
2.53	
.14	-
2.42	
.14	-
2.47	
.14	-
2.63	
.14	-
2.53	
.14	-
2.78	
.14	-
33.60	T

DUP050094647