

HARDNESS 60+/-5

STOCK NO. 03271 -1

AKRO 56602

COMPOUNDED BY

05/15/90

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
001	VINYL RESIN	100.00	71.94	33.90	200.00
006	DINP	80.00	80.81	27.12	160.00
017	MERROL E-68	3.00	3.03	1.01	6.00
030	VICRON 15-15	100.00	37.04	33.90	200.00
032	UNITANE OR-560	3.90	.98	1.32	7.80
146	SYNPRON 1530	2.00	1.92	.67	4.00
172	LR-8499 RED	3.00	1.79	1.01	6.00
179	E-8850 BROWN OXIDE	2.25	.59	.76	4.49 A
180	E-8851 BROWN OXIDE	.75	.20	.25	1.50 A

105 180 169 16

TOTAL	294.90	198.30	99.99	589.79
-------	--------	--------	-------	--------

.79	-	PHYSICAL PROPERTIES
USE	-	SPEC. MIN. MAX.
REPLACES	-	SPECIFIC GR. 1.487
REASON	-	HARDNESS
COLOR	-	TENSILE
REQUIRMENTS TO MEET	-	ELONGATION
	-	MODULUS @
	-	MOONEY @
	-	SCORCH
	-	CURE

STOCK CONTROL TEST

LAB
COST
MIXING

CHARD0 01180

HARDNESS 60+/-5

STOCK NO. 03271 -2

AKRO 56602

COMPOUNDED BY

04/23/91

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
001	VINYL RESIN	100.00	71.94	33.73	200.00
006	DINP	80.00	80.81	26.99	160.00
017	MERROL E-68	3.00	3.03	1.01	6.00
030	VICRON 15-15	100.00	37.04	33.73	200.00
032	UNITANE OR-560	3.90	.98	1.31	7.80
146	SYNPRON 1530	2.00	1.92	.67	4.00
172	LR-8499 RED	3.00	1.79	1.01	6.00
179	E-8850 BROWN OXIDE	2.25	.59	.75	4.50
180	E-8851 BROWN OXIDE	1.75	.46	.59	3.50 C
105	PENN COLOR 8313-575 BLACK	.50	.38	.16	1.00 A

TOTAL	296.40	198.94	99.99	592.80
-------	--------	--------	-------	--------

.81	-	PHYSICAL PROPERTIES
	-	SPEC. MIN. MAX.
USE	-	SPECIFIC GR. 1.490
	-	HARDNESS
REPLACES	-	TENSILE
	-	ELONGATION
REASON	-	MODULUS @
	-	MOONEY @
COLOR	-	SCORCH
	-	CURE
REQUIRMENTS TO MEET	-	STOCK CONTROL TEST
LAB	-	
COST	-	
MIXING	-	

CHARDO 01181

3272

HARDNESS 90 90+

STOCK NO. 03272

SPLASH SHIELD W/FUNGICIDE

COMPOUNDED BY

03/05/96

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
001	VINYL RESIN	99.98	71.93	43.63	199.96
006	PLATINAL 79-P (DINP)	59.99	60.60	26.18	119.98
017	MERROL E-68 (ESO)	3.00	3.03	1.30	6.00
030	VICRON 15-15	59.99	22.22	26.18	119.98
032	TiO2 R-902	3.00	.75	1.30	6.00
053	STEARIC ACID DP	.25	.31	.10	.50
069	VANCIDE 89	.50	.30	.21	1.00
108	CS-100-30 VIOLET	.40	.34	.17	.80
146	SYNPRON 1971	2.00	1.92	.87	4.00

TOTAL	229.11	161.40	99.99	458.22
.59	-	PHYSICAL PROPERTIES		
USE	-	SPEC.	MIN.	MAX.
REPLACES	-	SPECIFIC GR.	1.420	
REASON	-	HARDNESS		
COLOR	-	TENSILE		
REQUIRMENTS TO MEET	-	ELONGATION		
	-	MODULUS @		
	-	MOONEY @		
	-	SCORCH		
	-	CURE		
	-	STOCK CONTROL TEST		
LAB	-			
COST	-			
MIXING	-			

CHARDO 01182

HARDNESS 90 90+

STOCK NO. 03272

SPLASH SHIELD W/FUNGICIDE

COMPOUNDED BY

03/05/96

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
001	VINYL RESIN	99.98	71.93	43.63	199.96
006	PLATINAL 79-P (DINP)	59.99	60.60	26.18	119.98
017	MERROL E-68 (ESO)	3.00	3.03	1.30	6.00
030	VICRON 15-15	59.99	22.22	26.18	119.98
032	TiO2 R-902	3.00	.75	1.30	6.00
053	STEARIC ACID DP	.25	.31	.10	.50
069	VANCIDE 89	.50	.30	.21	1.00
108	CS-100-30 VIOLET	.40	.34	.17	.80
146	SYNPRON 1971	2.00	1.92	.87	4.00

TOTAL	229.11	161.40	99.99	458.22
-------	--------	--------	-------	--------

.59	-	PHYSICAL PROPERTIES
	-	SPEC. MIN. MAX.
USE	-	SPECIFIC GR. 1.420
	-	HARDNESS
REPLACES	-	TENSILE
	-	ELONGATION
REASON	-	MODULUS @
	-	MOONEY @
COLOR	-	SCORCH
	-	CURE
REQUIRMENTS TO MEET	-	STOCK CONTROL TEST
LAB	-	
COST	-	
MIXING	-	

CHARDO 01183