

VISCOSITY WORK SHEET

Item 861-866 P.T.No. _____ Date 1/20/56
 Worker Stanley Polymer Lucite Solvent CHCl₃
 For Camelion Charge 1329 Temperature 20°C
 Viscometer No. III Efflux Time 151.8, 152.0 Weight: Gross 3.6076
 Viscometer No. 8 Efflux Time 159.6, 159.1 Tare 3.4826
 Viscometer No. A Efflux Time 170.1, 170.2 Net 0.1250

Sample Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh. Visc. or M.W.	
5146-32A	VI	III	189.5; 189.5	1.247	0.44 ✓
5146-32B	X	8	199.3; 199.3	1.249	0.44 ✓
5146-32C	00	A	214.7; 214.8; 214.8	1.262	0.47 ✓
5146-32D	10	III	190.9; 190.8; 190.7	1.258	0.46 ✓
5146-33A	DX	8	200.7; 200.2; 200.5	1.258	0.46 ✓
5146-33B	0-1	A	215.8; 214.9; 214.7	1.262	0.47 ✓

PC-1

N38874

1-23-56
may

cl
JK