

FROM J. E. Southwick DATE June 27, 1972
CITY Coatings & Resins Research Center
Strongsville, Ohio

FOR Mr. S. T. Howell

CC: Mr. R. J. Haviland, #1
Mr. H. M. Werner, UCB
Mr. M. W. Malaga, #1
Mr. J. G. Kingston
Mr. W. M. Tomc

ANSWERING LETTER OF

SUBJECT Lead Removal - Y-999A - Spred Gloss Primer
Y-5229E - Galvanized Metal Primer

The subject formulas have been changed to remove lead driers and lead feed driers. Calcium, cobalt and zirconium is the recommended drier combination for equal dry. The cost increase is 1¢/gal. for Y-5229E and 1.8¢ for Y-999A.

JES:jm

J. E. Southwick

GLD007175