MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE YE698 LOT 40047

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	76	3,800		
	STUMP	Lumps 3725		

TOTAL NET WT. 3,800 PKG. N–CODE 1000

PROD. SPVR. DATE WHSE. OPER.

5/20/81

DUP050095749

DUP050095750

93/211

CG 01 CODE YE-698-D PKG.

APR -0-81- 40047

EST. WGT. 3371 LBS.

Grind into Totes Per. W.Z.

OK/LP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YE-698-D (R)	JMC 11-18-
(E) YC-10-B	DCG 11-18-
TYPED BY	
JLC 11-24-76	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
AT	241				
ATE	4/9/81				
IME	700				
ELEASED BY	[illegible]				
RESS	2	91	92	93	
O. OF CAKES	32	42	32	32	
RESS	with	AGITATION			
ASH TO	2000	OHMS with 35-75°F water			
EST AFTER	2	HOURS			
OAD on 4 cars					

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	8 AM				
CAKES USED	32				
WATER ON	1250 PM				
HRS. WASHED	3				
OHMS	486				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	471				

EXPLAIN LOSSES

AMPLES

ELIVER TO

BLL

SAMPLED BY

RELEASED BY

-DRYING-

EXTRUDED) DRY 12 HOURS AT 240°F

NOT EXTRUDED) DRY 14 HOURS AT 240°F

LUMP: - OK - WET - SALTS - CONTAMINAT

Color appears dry Possible Color left on Extruder from Prev Batch.

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 11

AMPLES

ELIVER TO

NO. CARS PULLED

LUMP WGT. 3725

SAMPLED BY

RELEASED BY

-GRINDING-

ILL Mikroatomize SCREEN RPM

AX. TEMP. °F

SCREEN RPM

MAX. TEMP. °F

SET ROOF BLAST GATE AT "9" FOR HIGH AIR FLOW

EXPLAIN LOSSES

AMPLE A[illegible] / WITHOUT MIXING

AMPLES 1 Env

ELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

40047
41
85

3.78	+
0.14	-
3.75	+
0.14	-
3.74	+
0.14	-
3.60	+
0.14	-
3.65	+
0.14	-
3.61	+
0.14	-
3.80	+
0.14	-
3.59	+
0.14	-
4.25	+
0.14	-
3.90	+
0.14	-
1.12	+
0.14	-
37.25	*

DUP050095751