

68 03 20 Code Trade Name Eagle-Picher Basic Silicate White Lead
5/13/68 Date Chemical Name Basic Silicate White Lead

1 Card No.

Prev. Code SUPPLIERS (Primary) 202 Basic Silicate White Lead

FORMULATING PARAMETERS

1.88 Gal./Cwt. @ 25° C Eagle-Picher Company
53.19 Lb./Gal. @ 25° C
100 Wt. % NVM
100 Vol. % NVM
100 Wt. % Pig.
100 Vol. % Pig.

OTHER CHARACTERISTICS

Coeff. of Exp.
TOC Flash
Pt. ° F.
Price/Lb.
Reason for Assignment New
Similar Codes 68 01 00
Advantages Over Similar Material Stain control in redwood and cedar
Codes Which May Become Overstock

HANDLING

Shipping Containers 50 lb. bags
Safety Label Codes No
Safety Precautions Contains Lead. Avoid breathing dust. Wash hands after handling.
Protect from Freezing No
Protect from Moisture No
Flammable Material No
Explosive Material No
Hazardous Material Yes
Age Limit of Material None

OTHER HANDLING INFORMATION

USES

Product Name Type or Rex A6 W 13
Line Item X Cust. Spec. Exper.

Instructions

1. Fill out as completely as possible. Laboratory requesting assignment must furnish complete information.
2. Enumerate all tests on opposite side in consecutive order.
3. Write special tests or procedures which may be necessary under special characteristics and tests.

The following test numbers are to be run routinely 1, 2, 3, 4
Tentative Reference Sample to be sent to Cleveland Tech. Service Yes No X

Chemist Requesting Assignment H. F. Henion Date 5/13/68

Laboratory Director Approving R. C. Hall Lab. D

0007-SWP-0048441

N15816

Code 68-0



THE SHERWIN-WILLIAMS Co.

GENERAL PURCHASING DEPT.

101 PROSPECT AVE., N.W.

CLEVELAND, OHIO 44101

SPECIFICATION FOR PURCHASED MATERIAL

Material Basic Silicate White Date 5/13/68 Code 68 03 20

Lead - Eagle Picher 202

Supersedes Specification

General Description:

Date

Code

White free flowing powder

CHARACTERISTICS	MIN.	STD.	MAX.	TEST METHOD
1. Color	Equal	to Standard		ASTM D 387
2. Texture	Equal	to Standard		
3. Oil-Absorption	17		19	ASTM D 281
4. Residue 325 Mesh			1.0	ASTM D 185
5. Moisture (%)			.75	ASTM D 280

SPECIAL TESTS AND/OR CHARACTERISTICS:

0007-SWP-0048442

PRACTICAL REQUIREMENTS: The material shall remain constant in successive lots or shipments with respect to unspecified characteristics to the extent that the seller warrants that no known changes are to be made in raw materials or processing methods of this material without

Code 68 03 20

RAW MATERIAL CHARACTERISTICS AND ASSIGNMENT REQUEST FORM

INTRA COMPANY CONFIDENTIAL

This Side for S-W and Affiliated Company Personnel Only

68 03 20 Code

TRADE NAME Eagle Picher Basic Silicate White Lead

9/4/68 Date

CHEMICAL NAME Basic Silicate White Lead

2 Card No.

Prev. Code

SUPPLIERS (Primary)

CODE

FORMULATING PARAMETERS

1.58 Gal. Cwt. @ 25° C

55.19 Lb./Gal. @ 25° C

100 Wt. % NVM

100 Vol. % NVM

100 Wt. % Pig.

100 Vol. % Pig.

Eagle Picher Company

202 Basic Silicate White Lead

OTHER CHARACTERISTICS

HANDLING

Coeff. of Exp.

Shipping Containers

50 lb. bags Safety Label Codes

No

TOC Flash

Age Limit

None

Protect from Freezing

No

Protect from Moisture

Yes

Pt. ° F.

Flammable Material

No

Explosive Material

No

Hazardous Material

Yes

Price Lb.

SAFETY PRECAUTIONS AND OTHER HANDLING INFORMATION

Contains lead. Avoid breathing dust. Wash hands after handling.

USES

Product Name Type or Rex

A6 W 13

Line Item

A

Customer Specification

Experimental

Reason for Assignment or Revision

Similar Codes

66 02 00

Codes Which May Become Overstock

Advantages Over Similar Material

Stair control in reduced and cedar

SPECIAL TESTS:

N15816.01

INSTRUCTIONS

0007-SWP-0048443

1. Fill out as completely as possible. Refer to Routine & Policy Bulletin No. 145.
2. Enumerate all tests on opposite side in consecutive order.

The following test numbers are to be run routinely. 2, 2, 3, 4

Tentative Reference Sample to be sent to Cleveland Tech. Service

Yes

No

X

Person Requesting Assignment

H. F. Henion

Date

9/4/68

Laboratory Coordinator Approving

E. C. Hall

Lab.

D

Received and Approved in Cleveland

By R. L. GARDNER/E. Gardiner

Date

9/24/68

Code 68 03 20



THE SHERWIN-WILLIAMS Co.

GENERAL PURCHASING DEPT. • 101 PROSPECT AVE., N.W. • CLEVELAND, OHIO 44101

SPECIFICATION FOR PURCHASED MATERIAL

Material Basic Silicate White Lead Date 9/1/68 Code 68 03 20

Supersedes Specification

General Description:

Date 5/13/68 Code 68 03 20

White free flowing powder for use as pigment in exterior paints.

CHARACTERISTICS	MIN.	STD.	MAX.	TEST METHOD
1. Color	Equal to	Standard		ASTM D 387
2. Texture	Equal to	Standard		
3. Oil Absorption	16		22	ASTM D 281
4. Residue 325 Mesh			1.0	ASTM D 185
5. Moisture (%)			1.5	ASTM D 280

SPECIAL TESTS AND/OR CHARACTERISTICS:

0007-SWP-0048444

PRACTICAL REQUIREMENTS: The material shall remain constant in successive lots or shipments with respect to unspecified characteristics to the extent that the seller warrants that no known changes are to be made in raw materials or processing methods of this material without due notification of the buyer.

Code 68 03 20