

MAY 26 1982

F2H59

(DATE)

(LOT)

NOTES:

TOTAL EST'D WGT = ~~2865~~ LBS

JOB NAME: 20BC002APC

INSTRUCTIONS		= PRESSING =	RECORD				
VAT	180	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	6-10-82	STARTED	2 PM				
TIME	12 PM	CAKES USED	44				
RELEASED BY	166	WATER ON	11				
PRESS	31	HRS. WASHED	22				
NO. OF CAKES	44	OHMS	260				
PRESS WITH AGITATION		HRS. WASHED					
WASH TO 3000 OHMS - 135-145°F WATER		OHMS					
TEST AFTER 20 HOURS		HRS. WASHED					
LOAD IN METAL DRUMS AT 360# NET WGT.		OHMS					
NOTE: 1. REQUEST MAKING REHEAT SV TO		CAKE CONDITION					
178-182°F ONCE PER SHIFT		NO CARS LOADED					
2. AIR-BLOW PRESSCAKE WHEN		EXPLAIN LOSSES					
3000 OHMS REACHED FOR 15 MIN.							
AT 40 PSI.							
SAMPLES THIEF SAMPLE PER 30P		SAMPLED BY					
DELIVER TO CTL		RELEASED BY					

= DRYING =

DO NOT DRY

 18 Drms 325#
 1 stp 45#

= GRINDING =

DO NOT GRIND

N39180