

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE YC-16 LOT K2H26

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

50 65 3250**STUMP** 4 mm 3290TOTAL NET WT. 3250 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

91 181

PRODUCT NAME: MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YC-16-B

FKG

PROCESSES
YC-16-B (C)

APPROVED BY:
FWP 09/22/81

LOT

K2H26

SEP 29 1967

COMTYP JOB NAME=01YC046BPC

EST. WT: 3098* LBS.

MAKING NOTES

INSTRUCTIONS

= PRESSING =

RECORD

VAT	245				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-4				STARTED	1:40 PM				
TIME	10:30 AM				CAKES USED	212				
RELEASED BY	[Signature]				WATER ON	4301				
PRESS	92	2	25		HRS. WASHED	4:41				
NO. OF CAKES	32	32	32		M MHOS	050				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER					M MHOS					
TEST AFTER 2 HOURS.					HRS. WASHED					
LOAD ON 4 CARS					M MHOS					
					CAKE CONDITION					
					NO CARS LOADED					
					EXPLAIN LOSSES	5				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 16 HOURS AT 220° F

LUMP - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO -

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 13
LUMP WGT 3290

= GRINDING

MIKROATOMIZE
SET ROOF GATE AT 2 INCHES AIR FLOW
SET LUMP FEED SCREW AT 1/2 SPEED
MAGNEHELIC READING ON ATOMIZER
PANEL 1.0'

SCREEN	RPM
MAX-TEMP	F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

26.
41
225

0.00 *

0.00 *

2.68 +

0.12 ✓

2.62 +

0.12 ✓

2.66 +

0.12 ✓

2.90 +

0.12 ✓

2.84 +

0.12 ✓

2.55 +

0.12 ✓

2.79 +

0.12 ✓

2.79 +

0.12 ✓

2.68 +

0.12 ✓

2.99 +

0.12 ✓

2.71 +

0.12 ✓

2.56 +

0.12 ✓

1.69 +

0.12 ✓

32.90 *

6-366.
8654